

Complete Machining Solutions

MATERIALS AND GRADES



ISCAR Milling Grades Chart

Grades	ISO	Coating Layers
IC300	P20-P40 M20-M35 S15-S30	TiCN
IC328	P25-P40 M30-M40 S20-S30	TiCN
S.T. IC330	P25-P40 M30-M40 S20-S30	TiN TiCN
S.T. IC380	S15-S20 H15-H25	TiN TiCN
IC608	P10-P20 M10-M20 K10-K25 H15-H25	TiSiN TiAlSiN AlTiN
S.T. IC808	P15-P30 M20-M30 K20-K30 S10-S25 H20-H30	TiN AlTiN
S.T. IC810	K15-K35 P15-P30	TiN AlTiCrN
S.T. IC830	P20-P40 M25-M35 S15-S30	TiN AlTiN
S.T. IC840	M20-M35 S15-S25	TiSiN TiAlSiN AlTiN
S.T. IC845	P25-P45	TiN AlTiN
S.T. IC882	M25-M40 S20-S30	TiSiN TiAlSiN AlTiN
IC900	P15-P30 M20-M30 K20-K30 S10-S25 H20-H30	AL-TEC AlTiN
IC902	P05-P15 M10-M15 K05-K15 S05-S10 H05-H15	AL-TEC AlTiN
IC903	H10-H20 P10-P20 M15-M25 K10-K20 S10-S20	AL-TEC AlTiN
IC908	P15-P30 M20-M30 K20-K30 S10-S25 H20-H30	AlTiN
IC910	P15-P30 K15-K35	AL-TEC AlTiN
IC928	P20-P40 M25-M35 S15-S30	AlTiN

S.T. SUMO TEC **■** PVD COATED **■** CVD COATED **■** UNCOATED **■** CERMET **■** CBN **■** PCD **■** SILICON NITRIDE

ISCAR Milling Grades Chart

Recommended Applications

A tough submicron TiCN **PVD** coated grade. Suitable for milling heat resistant alloys, austenitic stainless steel and steel at unfavorable conditions, at low to medium cutting speeds.

A TiCN **PVD** coated tough grade.

Used for a wide range of workpiece materials, at low to medium cutting speeds.

A TiCN **PVD** coated tough grade. Used for milling, grooving, parting and drilling a wide range of workpiece materials, at low to medium cutting speeds.

A tough submicron substrate, TiCN **PVD** coated and a special surface treatment. Designed for machining titanium and heat resistant alloys, austenitic stainless steel, at medium to high cutting speeds, interrupted cut and unfavorable conditions. Excellent notch wear and built-up edge resistance. High resistance to mechanical and thermal shock – therefore milling with coolant may be applied.

Tough submicron substrate with hard **PVD** coating.

Suitable for milling hardened steel (45-60 HRC), alloy steel and stainless steel at moderate to high cutting speed.

A tough submicron substrate, AlTiN **PVD** coated multi-purpose grade. Designed for machining hard alloy and carbon steel, heat resistant alloys and austenitic stainless steel, at medium to high cutting speeds, interrupted cut and unfavorable conditions. Excellent notch wear and built-up edge resistance.

A PVD AlTiCrN coated grade. First choice for milling nodular cast iron at medium to high cutting speeds.

A PVD AlTiN coated tough grade. Suitable for milling steel, stainless steel and high temperature alloys.

Recommended for interrupted cut and heavy operations.

A hard multilayered **PVD** coating with tough substrate.

For successful milling of stainless steel, titanium and high-temperature alloys.

A PVD AlTiN coated tough substrate.

This grade recommended for milling steel at moderate to high cutting speeds and for interrupted applications.

A hard multilayered **PVD** coating with tough substrate.

For successful milling of stainless steel, titanium and high-temperature alloys espically for interrupted applications.

A tough, submicron **PVD** AlTiN coated grade. Suitable for milling heat resistant alloys, austenitic stainless steel, hard alloys and carbon steel at medium to high cutting speeds.

Ultra-fine grain carbide with AlTiN **PVD** coating.

Used for up to 62 HRC hardened steel, titanium, nickel-based alloys and stainless steel at high speeds and medium feeds

A carbide grade with ultra-fine grain substrate and AlTiN **PVD** coating. Used for up to 62 HRC hardened steel, titanium, nickel-based alloys and stainless steel at high speeds and medium feeds. A tough and highly wear resistant grade.

A tough submicron substrate, TiAlN **PVD** coated multi-purpose grade. Designed for machining carbon steel and austenitic stainless steel, at medium to high cutting speeds, interrupted cut and unfavorable conditions.

Excellent notch wear and built-up edge resistance.

A PVD AlTiN coated grade. Suitable for milling nodular cast iron at medium to high cutting speeds.

A PVD TiAlN coated tough grade.

Suitable for milling alloy steel, stainless steel. Recommended for interrupted cut and heavy operations.

ISCAR Milling Grades Chart

Grades	ISO	Coating Layers
S.T. IC5100	K10-K25	a-TEC
S.T. IC5400	P01-P20 M10-M25	
S.T. IC5500	P20-P35	
S.T. IC5820	M20-M35 S15-S25	
DT7150 CVD+PVD COATED	K10-K25 H20-H30	DO-TEC

IC07	M10-M20 S10-S30 N05-N20	
IC08	N10-N20	
IC30N	P10-P30 M10-M20 H10-H25	
IB55	K05-K15 H10-H25	
IB85	K01-K15 H05-H10 S05-S10	
ID5	N01-N10	
IS8 SILICON NITRIDE	K01-K15	

S.T. SUMO TEC **■** PVD COATED **■** CVD COATED **■** UNCOATED **■** CERMET **■** CBN **■** PCD **■** SILICON NITRIDE

ISCAR Milling Grades Chart

Recommended Applications

A tough substrate with a **MTCVD** and TiCN/Al₂O₃ coating. Recommended for milling grey cast iron at high cutting speeds, providing extended tool life.

A tough substrate with a **MTCVD** and alpha Al₂O₃ coating. Recommended for milling steel at high cutting speed providing excellent tool life.

A tough substrate with a **MTCVD** and alpha Al₂O₃ coating. Recommended for milling martensitic stainless steel at high cutting speed.

A tough substrate with a **MTCVD** and alpha Al₂O₃ coating and a special surface treatment. Designed for machining austenitic stainless steel, titanium and high temperature alloys, especially for applying high-pressure coolant (**HPC**) supply.

A tough substrate with a dual **MTCVD** Al₂O₃ and TiAlN **PVD** coating. Recommended for medium to high cutting speeds for machining cast iron, especially hard special-purpose cast iron grades. Features high wear and chipping resistance.

An uncoated, fine grain carbide grade for machining mainly **ISO N** materials in a wide range of cutting speeds. Used for high temperature alloys and stainless steel at low to medium cutting speeds.

An uncoated, fine grain carbide grade. Used for stainless steel and high temperature alloys at low to medium cutting speeds.

A cermet grade. Provides excellent resistance to wear and plastic deformation even at high cutting speeds and medium feeds. Useful for turning and milling of semi-finishing and finishing applications.

A 55% **CBN** brazed tip, used for finishing hardened steel and cast iron (45-65 HRC) in continuous cutting.

An 85% **CBN** brazed tip, used for high speed machining of cast iron, cemented tungsten carbide, sintered metals and heavy alloys.

Excellent for interrupted cutting of hardened steel.

A **PCD** brazed tip, suitable for machining aluminum (Si < 12%) and copper alloys and general cutting of nonferrous materials.

A silicon nitride grade, intended mainly for medium-duty turning and milling applications. Can be used for interrupted cuts.

MATERIAL GROUPS**According to DIN / ISO 513 and VDI 3323**

ISO	Material	Condition	Tensile Strength [N/mm ²]	Kc ⁽¹⁾ [N/mm ²]	mc ⁽²⁾	Hardness HB	Material No.	
P	Non-alloy steel and cast steel, free cutting steel	< 0.25 %C	Annealed	420	1350	0.21	125	1
		=> 0.25 %C	Annealed	650	1500	0.22	190	2
		< 0.55 %C	Quenched and tempered	850	1675	0.24	250	3
		>= 0.55 %C	Annealed	750	1700	0.24	220	4
			Quenched and tempered	1000	1900	0.24	300	5
	Low alloy steel and cast steel (less than 5% of alloying elements)	Quenched and tempered	Annealed	600	1775	0.24	200	6
			930	1675	0.24	275	7	
			1000	1725	0.24	300	8	
			1200	1800	0.24	350	9	
	High alloyed steel, cast steel, and tool steel	Annealed	680	2450	0.23	200	10	
		Quenched and tempered	1100	2500	0.23	325	11	
M	Stainless steel and cast steel	Ferritic/martensitic	680	1875	0.21	200	12	
		Martensitic	820	1875	0.21	240	13	
M	Stainless steel	Austenitic, duplex	600	2150	0.20	180	14	
K	Grey cast iron (GG)	Ferritic/pearlitic		1150	0.20	180	15	
		Pearlitic		1350	0.28	260	16	
	Nodular cast iron (GGG)	Ferritic		1225	0.25	160	17	
		Pearlitic		1350	0.28	250	18	
	Malleable cast iron	Ferritic		1225	0.25	130	19	
		Pearlitic		1420	0.3	230	20	
N	Aluminum-wrought alloy	Not hardenable		700	0.25	60	21	
		Hardenable		800	0.25	100	22	
	Aluminum-cast, alloyed	Not hardenable		700	0.25	75	23	
		Hardenable		700	0.25	90	24	
		>12% Si	High temperature	750	0.25	130	25	
		>1% Pb	Free cutting	700	0.27	110	26	
	Copper alloys		Brass	700	0.27	90	27	
			Electrolytic copper	700	0.27	100	28	
	Non metallic	Duroplastics, fiber plastics					29	
			Hard rubber				30	
S	High temperature alloys	Fe based	Annealed	2600	0.24	200	31	
			Hardened	3100	0.24	280	32	
		Ni or Co based	Annealed	3300	0.24	250	33	
			Hardened	3300	0.24	350	34	
	Titanium alloys	Cast		3300	0.24	320	35	
		Pure	RM 400	1700	0.23		36	
		Alpha+beta alloys hardened	RM 1050	2110	0.22		37	
H	Hardened steel	Hardened		4600		55 HRC	38	
		Hardened		4700		60 HRC	39	
	Chilled cast iron	Cast		4600		400	40	
	Cast iron	Hardened		4500		55 HRC	41	


 Steel  Stainless Steel  Cast Iron

 Nonferrous  High Temp. and Titanium Alloys  Hardened Steel and Cast Iron

(1) Specific cutting force for 1 mm² chip section. (see page 523).

(2) Chip thickness factor. (see page 523).

Hardness Conversion Table



MATERIAL GROUPS

According to VDI 3323 Standard

	 USA	 GERMANY	 Great Britain		
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS	EN
1		1.0028	Ust 34-2 (S250G1T)		
1		1.0034	RSt 34-2 (S250G2T)	1449 34/20HR; 1449 34/20HS; 1449 34/20CR; 1449 34/20CS	
1		1.0035	St185 (Fe 310-0); St 33	Fe 310-0; 1449 15HR; 1449 15HS	
1	A 570 Gr. 33; A 570 Gr. 36	1.0036	S235JRG1; (Fe 360 B); Ust 37-2	Fe 360 B; 4360-40 B	
1		1.0037	S235JR (Fe 360 B); St 37-2	Fe 360 B; 4360-40 B	
1	A 570 Gr. 40	1.0044	S275JR (Fe 430 B); St44-2	Fe 430 B FN; 1449 43/25 HR; 1449 43/25HS; 4360-43 B	
1		1.0045	S355JR	4360-50 B	
1	A 570 Gr.50; A 572 Gr.50	1.0050	E295 (Fe 490-2); St 50-2	Fe 490-2 FN; 4360- 50 B	
1	A 572 Gr. 65	1.0060	E335 (Fe 590-2); St 60-2	Fe 60-2; 4360-55 E; 4360-55 C	
1		1.0112	P235S	1501-164-360B LT20	
1		1.0114	S235JU; St 37-3 U	4360-40C	
1		1.0130	P265S	1501-164-400B LT 20	
1		1.0143	S275J0; St 44-3 U	4360-43C	
1	A 573 Gr. 70; A 611 Gr.D	1.0144	S275J2G3 (Fe 430 D 1); St 44-3	Fe 430 D1 FF; 4360- 43 C; 4360-43 D	
1		1.0149	S275JOH; RoSt 44-2	4360-43C	
1		1.0226	DX51D; St 02 Z	Z2	
1	M 1010	1.0301	C10	040 A 10; 045 M 10; 1449 10 CS	
1	A 621 <small>(1008)</small>	1.0330	DC 01; St 2; St 12	1449 4 CR; 1449 3 CS	
1	A 619 <small>(1008)</small>	1.0333	Ust 3 (DC03G1); Ust 13	1449 2 CR; 1449 3 CR	

					
A 34-2		Fe 330; Fe 330 B FU		SS 330	
A 34-2 NE		Fe 330 B FN			St2sp; St2ps
A 33	1300	Fe 320	Fe 310-0		St0
	1311; 1312	FE37BFU	AE 235 B; Fe 360 B		16D; 18kp; St3kp
E 24-2	1311	Fe 360 B; 1449 37/23 HR	AE 235 B; Fe 360 B	STKM 12 A; STKM 12 AC	
E 28-2	1412	Fe 430 B; Fe 430 B FN	AE 275 B; Fe 430 B FN	SM 400 A; SM 400 B; SM 400 C	St4ps; St4sp
E 36-2	2172	Fe 510 B	AE 355 B		
A 50-2	1550; 2172	Fe 490	a 490-2; Fe 490-2 FN	SS 490	ST5ps; ST5sp
A 60-2	1650	Fe 60-2; Fe 590	A 590-2; Fe 590-2 FN	SM 570	St6ps; St6sp
A37AP		Fe 360 C	AE 235 C		
E 24-3		Fe 360 C	AE 235 C		
A 42 AP			SPH 265		
E 28-3	1414-01	Fe 430 D	AE 275 D		
E 28-3; E 28-4	1411; 1412; 1414	Fe 430 B; Fe 430 C (FN); Fe 430 D (FF)	AE 275 D; Fe 430 D1 FF	SM 400 A; SM 400 B; SM 400 C	St4kp; St4ps; St4sp
	1412-04	Fe 430 C	Fe 430 C		
GC	1151 10	FeP 02 G	FeP 02 G		
AF 34 C 10; XC 10		C 10; 1 C 10	F.1511; F.151.A	S 10C	10
TC	1142	FeP 00; FeP 01	AP 11	SPHD	15 kp
E		FeP 02	AP 02	SPCD	

MATERIAL GROUPS

According to VDI 3323 Standard

	 USA	 GERMANY	 Great Britain		
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS	EN
1	A 621 <small>(1008)</small>	1.0334	UStW 23 <small>(DD12G1)</small>		
1	A 622 <small>(1008)</small>	1.0335	DD13; StW 24	1449 1 HR	
1	A 620 <small>(1008)</small>	1.0338	DC04; St 4; St 14	1449 1 CR; 1449 2 CR	
1	A 516 Gr. 65; 55 A 515 Gr. 65; 55 A 414 Gr. C; A 442 Gr.55	1.0345	P235GH/H I	1501 Gr. 141-360; 1501 Gr. 161-360; 151-360 1501 Gr. 161-400; 154-360 1501 Gr. 164-360; 161-360	
1	(M) 1020; M 1023	1.0402	C22	055 M 15; 070 M 20; 1499 22 HS; 1499 22 CS	2C/2D
1	1020	1.0402	C22	050A20	2C/2D
1	1020; 1023	1.0402	C22	055 M 15; 070 M 20	2C
1		1.0425	P265GH/H II	1501 Gr. 161-400; 151-400 1501 Gr. 164-360; 161-400 1501 Gr. 164-400; 154-400	
1	A27 65-35	1.0443	GS-45	A1	
1		1.0539	S355NH;StE 355		
1		1.0545	S355N; StE 355	4360-50E	
1		1.0546	S355NL;TStE 355	4360-50EE	
1		1.0547	S355JOH	4360-50C	
1		1.0549	S355 NLH;TStE 355		
1		1.0553	S355JO;St 52-3U	4360-50C	
1	A 633 Gr.C; A 588	1.0562	P355N; StE 355	1501 Gr.225-490A LT 20	
1		1.0565	P355NH; WStE 355	1501-225-490B LT 20	
1		1.0566	P355NL1; TStE 355	1501-225-490A LT 50	
1	1	1.0570	S355J2G3; St 52-3	Fe 510 D1 FF; 1449 50/35 HR·HS; 4360-50 D	
1	1213	1.0715	9 SMn 28 <small>(1SMn30)</small>	230 M 07	

 France AFNOR	 Sweden SS	 Italy UNI	 Spain UNE	 Japan JIS	 Russia GOST
S C		FeP 12	AP 12	SPHE	10kp
3 C		FeP 13	AP 13	SPHE	08kp
ES	1147	FeP 04	AP 04	SPCE	08Ju; JuA
A 37 CP; A 37 AP	1331; 1330	FeE235; Fe 360 1 KW; Fe 360 1KG; Fe 360 2 KW; Fe 360 2 KG	A 37 RC I; RA II	SGV 410; SGV 450; SGV 480; SPV 450; SPV 480	
AF 42 C 20; XC 25; 1 C 22	1450	C 20; C 21; C 25	1 C 22; F.112	S20C	20
CC20	1450	C20; C21	F.112	S22 C	20
AF 42 C 20; XC 25; 1 C 22	1450	C 20;C 21;C 25	1 C 22F.112	S 20 C; S 22 C	
A 42 CP; A 42 AP	1431; 1430; 1432	Fe 410 1KW; Fe 410 1KG; Fe 410 1KT; Fe 410 2KW; Fe 410 2KG	A 42 RC I; A 42 RC II	SPV 315; SPV 355; SG 295; SGV 410; SGV 450; SGV 480	16K; 20K
E 23-45 M	1305				
TSE 355-4	2134-04	Fe 510 B	Fe 355 KGN		
E 355 R	2334-01	FeE 355 KG	AE 355 KG		
E 355 FP	2135-01	FeE 355 KT	AE 355 KT		
TSE 355-3	2172-04	Fe 510 C	Fe 510 C		
	2135	Fe 510 D	FeE 355 KTM		
E 36-3		Fe 510 C			
FeE 355 KG N; E 355 R/FP; A 510 AP	2106	FeE 355 KG; FeE 355 KW	AEE 355 KG; AEE 355 DD	SM 490 A; SM 490 B; SM 490 C; SM 490 YA; SM 490YB	15GF
A 510 AP	2106	FeE 355-2			
A 510 FP	2107-01	FeE 355-3			
E 36-3; E 36-4	2132; 2133; 2134; 2174	17GS; 17G1S	AE 355 D; Fe 510 D1 FF	SM 490 A; SM 490 B; SM 490 C; SM 490 YA; SM 490YB	17GS; 17G1S
S 250	1912	CF SMn 28	F.2111 - 11 SMn 28	SUM 22	

MATERIAL GROUPS**According to VDI 3323 Standard**

	 USA	 GERMANY		 Great Britain
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS EN
1	1213	1.0715	9 SMn 28	230 M 07
1	12 L 13	1.0718	9 SMnPb 28 (11SMnPb30)	
1	1108; 1109	1.0721	10 S 20	10S20
1	11 L 08	1.0722	10 SPb 20	
1	11 L 08	1.0722	10 SPb 20	
1	1215	1.0736	9 SMn 36 11SMn37)	
1	12 L 14	1.0737	9 SMnPb 36 (11SMnPb37)	
1		1.0972	S315MC; QStE 300 TM	1501-40F30
1		1.0976	S355MC; QStE 360 TM	1501-43F35
1		1.0982	S460MC; QStE 460 TM	1501-50F45
1		1.0984	S500MC; QStE 500 TM	
1		1.0986	S500MC; QStE 500 TM	1501 - 60F55
1	1010	1.1121	CK 10; (C10E)	040 A 10
1		1.1121	St 37-1	4360 40 A
1	1015	1.1141	CK 15; (C15E)	040 A 15; 080 M 15
1	1020; 1023	1.1151	C22E; CK 22	055 M 15; (070 M 20)
1		1.2083		
1	A572-60	1.8900	StE 380	4360 55 E
1	A36		St 44-2	4360 43 A
1			StE 320-3Z	1 501 160
2	(M) 1025	1.0406	C 25	070 M 26
2		1.0416	GS-38	
2	A 537 Cl.1; A 414 Gr. G; A 612	1.0473	P355GH; 19 Mn 6	
2	1035	1.0501	C35	080 A 32; 080 A 35; 080 M 36; 1449 40 CS
2	1045	1.0503	CF 45; (C45G)	060 A 47; 080 M 46

 France AFNOR	 Sweden SS	 Italy UNI	 Spain UNE	 Japan JIS	 Russia GOST
S 250	1912	CF 9 SMn 28	11 SMn 28	SUM 22	
S 250 Pb	1914	CF 9 SMnPb 28	F.2112-11 SMnPb 28	SUM 22 L; SUM 23 L; SUM 24 L	
10S20; 10 F 2		CF 10 S 20	F. 2121 - 10 S 20		
10PbF 2		CF 10 SPb 20	F.2122-10 SPb 20		
10 PbF 2		CF 10 SPb 20	10 SPb 20		
S 300		CF 9 Mn 36	F.2113 - 12 SMn 35	SUM 25	
S 300 Pb	1926	CF 9 SMnPb 36	F.2114- 12 SMnPb 35		
E 315 D					
E 355 D	2642	FeE 355TM			
E 490 D	2662	FeE 490 TM			
E 560 D		FeE 560 TM			
XC 10	1265	C 10; 2 C 10; 2 C 15	F-1510-C 10 K	S 9 CK; S 10 C	08;10
	1300				
XC 12; XC 15; XC 18	1370	C 15; C 16	F.1110-C 15 K; F.1511-C 16 K	S 15; S 15 CK	15
2 C 22; XC 18; XC 25	1450	C 20; C 25	F.1120-C 25 K	S 20 C; S 20 CK; S 22 C	20
	2314				
	2145	FeE390KG		S25C	
NFA 35-501 E 28	1411				
	1421				
1 C 25		C 25; 1 C 25			
20-400 M	1306				
A 52 CP	2101; 2102	Fe E 355-2	A 52 RC I, RA II	SGV 410; SGV 450; SGV 480	
1 C 35; AF 55 C 35; XC 38	1572; 1550	C 35; 1 C 35	F.113	S 35 C	35
XC 42 H 1 TS	1672	C 43; C 46		S 45 C	45

MATERIAL GROUPS**According to VDI 3323 Standard**

	 USA	 GERMANY		 Great Britain	
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS EN	
2	1040	1.0511	C40	080 M 40	
2		1.0540	C 50		
2	A27 70-36	1.0551	GS-52	A2	
2	A148 80-40	1.0553	GS-60	A3	
2	A738	1.0577	S355J2G4 (Fe 510 D 2)	Fe 510 D2 FF; 1501 Gr.224-460; 1501 Gr. 224-490	
2	1140	1.0726	35 S 20	212 M 36	8M
2	1146	1.0727	45 S 20 (46S20)		
2	1035; 1041	1.1157	40Mn4	150 M 36	15
2	1025	1.1158	C25E; CK 25	(070 M 25)	
2	1536	1.1166	34Mn5		
2	1330	1.1170	28Mn6	(150 M 28); (150 M 18)	14A
2		1.1178	C30E; CK 30	080M30	
2	1035	1.1180	C35R; Cm 35	080 A 35	
2	1035; 1038	1.1181	C35E; CK 35	080 A 35; (080 M 36)	
2	1035	1.1181	C35E; CK 35	080 A 35; (080 M 36)	
2	1035	1.1183	Cf 35 (C35G)	080 A 35	
2	1042	1.1191	GS- Ck 45	080 A 46	
2	1049; 1050	1.1206	C50E; CK 50	080 M 50	
2	1050; 1055	1.1213	Cf 53; (C53G)	070 M 55	
2	4520	1.5423	22Mo4	1503-245-420	
3	A 516 Gr.70; A 515 Gr. 70; A 414 Gr.F; A 414 Gr.G	1.0481	P295GH; 17 Mn 4	1501 Gr. 224	

 France AFNOR	 Sweden SS	 Italy UNI	 Spain UNE	 Japan JIS	 Russia GOST
1 C 40; AF 60 C 40		C40; 1 C 40	F.114.A		
	1674	C 50	1 C 50		
280-480 M	1505				
320-560 M	1606				
A 52 FP	2107		A 52 RB II; AE 355 D		
35MF 6	1957		F.210.G		
45 MF 4	1973				
35 M 5; 40 M 5					40G
2 C 25; XC 25		C25	F.1120 - C 25 K	S 25 C; S 28 C	25
			TO.B	SMn 433 H	
20 M 5; 28 Mn 6		C 28 Mn	28 Mn 6	SCMn 1	30G
XC 32		C 30	2 C 30		
3 C 35; XC 32	1572		F.1135-C 35 K-1		
2 C 35; XC 32; XC 38 H 1	1550; 1572	C 35	F.1130-C 35 K	S 35 C	35
XC 38	1572	C36		S35C	
XC 38 H 1 TS	1572	C 36; C 38		S 35 C	35
XC 45	1660	C45	F-1140		
2 C 50; XC 48 H 1; XC 50 H 1	1674	C 50			50
XC 48 H TS	1674	C 53		S 50 C	50
		16 Mo 5 KG; 16 Mo 5 KW	F.2602- 16 Mo 5	SB 450 M; SB 480 M	
A 48 CP; A 48 AP		Fe 510 KG; Fe 510 KT; Fe 510 KW; Fe 510-2 KG; Fe 510-2KT; Fe 510-2KW; FeE 295	A 47 RC I; RA II	SG 365; SGV 410; SGV 450; SGV 480	14G2

MATERIAL GROUPS**According to VDI 3323 Standard**

	 USA	 GERMANY		 Great Britain
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS EN
3	1043	1.0503	C35	060 A 47; 080 M 46; 1449 50 HS, 1449 50 CS
3	1074	1.0614	C 76 D; D 75-2	
3	1086	1.0616	C 86 D; D 85-2	
3	1095	1.0618	C 92 D; D 95-2	
3	1036; 1330	1.1165	30Mn5	120 M 36; (150 M 28)
3	1335	1.1167	36Mn5	150 M 36
3	1040	1.1186	C40E; CK 40	060 A 40; 080 A 40; 080 M 40
3	1045	1.1191	C45E; CK 45	080 M 46; 060 A 47
3	1049	1.1201	C45R; Cm 45	080 M 46
3		1.7242	18 CrMo 4	
3	A 387 Gr. 12 Cl	1.7337	16 CrMo 4 4	
3		1.7362	12 CrMo 19 5	3606-625
3	A572-60		17 MnV 6	436055 E
4	1055	1.0535	C55	070 M 55
4	1060	1.0601	C60	060 A 62; 1449 HS; 1449 CS 43D
4	107	1.0603	C67	080 A 67; 1449 70 HS
4	1074; 1075	1.0605	C75	1449 80 HS
4	1055	1.1203	C55E; CK 55	060 A 57; 070 M 55
4	1055	1.1209	C55R; Cm 55	070 M 55
4	1060; 1064	1.1221	C60E; CK 60	060 A 62 43D
4	1070	1.1231	Ck 67; (C67E)	060 A 67
4	1074; 1075; 1078	1.1248	CK 75; (C75E)	060 A 78
4	1086	1.1269	CK 85 (C85E)	

France AFNOR	Sweden SS	Italy UNI	Spain UNE	Japan JIS	Russia GOST
1 C 45; AF 65 C 45	1672; 1650	C 45; 1 C 45	F.114	S 45 C	45
XC 75					
XC 80		C 85			
XC 90					
35 M 5			F.8211-30 Mn 5; f.8311-AM 30 Mn 5	SMn 433 H; SCMn 2	27ChGSNMDTL 30GSL
40 M 5	2120		F. 1203-36 Mn 6; F. 8212-36 Mn 5	ssmN 438 (H); SCMn 3	35G2; 35GL
2 C 40; XC 42 H 1		C 40		S 40 C	
2 C 45; XC 42 H 1; XC 45; XC 48 H 1	1672	C 45; C 46	F.1140-C 45 K; F.1142-C48 K	S 45 C; S 48 C	45
3 C 45; XC 42 H 1; XC 48 H 1	1660	C 45	F.1145-C 45K-1; F.1147C 48 K-1	S 50 C	
		A 18 CrMo 4 5 KW			15ChM
Z 10 CD 5.05		16 CrMo 20 5			
NFA 35-501 E 36	2142				
1 C 55; AF 70 C 55	1655	C 55; 1 C 55		S 55 C	55
1 C 60; AF 70 C 55		C 60; 1 C 60		S 58 C	60(G)
XC 65		C 67			
		C 75			75
2 C 55; XC 55 H 1	1655	C 55	F.1150-C 55 K	S 55 C	55
3 C 55; XC 55 H 1		C 55	F.1155-C 55K-1		
2 C 60; XC 60 H 1	1665; 1678	C 60		S 58 C	60; 60G; 60GA
XC 68	1770	C70			65GA; 68GA; 70
XC 75	1774	C 75			75(A)
XC 90		C 90			85(A)

MATERIAL GROUPS

According to VDI 3323 Standard

	 USA	 GERMANY		 Great Britain
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS EN
4	1095	1.1274	Ck 101 (C101E)	
4	W 112	1.1663	C 125 W	
4				
5		1.0070	E360 (Fe 690-2); St 70-2	Fe 690-2 FN
5		1.7238	49 CrMo 4	
5		1.7701	51 CrMoV 4	
6	A 284 Gr.D; A 573 Gr.58; A 570 Gr 36; A 570 Gr C; A 611 Gr. C	1.0116	S235J2G3 (Fe 360 D 1); St 37-3	Fe 360 D1 FF; 1449 37/23 CR; 4360- 40 D
6	5120	1.0841	St 52-3	150 M 19
6	9255	1.0904	55 Si 7	250A53 45
6	9254	1.0904	55 Si 7	250 A 53
6	9262	1.0961	60SiCr7	
6	L3	1.2067	100Cr6	BL3
6	L1	1.2108	90 CrSi 5	
6	L2	1.2210	115CrV3	
6		1.2241	51CrV4	
6		1.2311	40 CrMnMo 7	
6	4135	1.2330	35 CrMo 4	708 A 37
6		1.2419	105WCr6	105WC 13
6	0 1	1.2510	100 MnCrW 4	BO1
6	S1	1.2542	45 WCrV7	BS1
6	S1	1.2550	60WCrV7	
6	L6	1.2713	55NiCrMoV6	
6	L 6	1.2721	50NiCr13	
6	O2	1.2842	90MnCrV8	BO2
6	E 50100	1.3501	100 Cr 2	
6	52100	1.3505	100Cr6	2 S 135; 535 A 99 31
6		1.5024	46Si7	
6	9255	1.5025	51Si7	
6	9255	1.5026	55Si7	251 a 58

 France AFNOR	 Sweden SS	 Italy UNI	 Spain UNE	 Japan JIS	 Russia GOST
XC 100	1870	C 100	F-5117	SUP 4	
Y2 120					
	2223				
A 70-2	1655	Fe 70-2; Fe 690	A 690-2; Fe 690-2 FN		
		51 CrMoV 4			
E 24-3; E 24-4	1312; 1313	Fe 360 D1 FF; Fe 360 C FN; Fe 360 D FF; Fe 37-2	AE 235 D; Fe 360 D1 FF		St3kp; St3ps; St3sp; 16D
20 MC 5	2172	Fe 52	F-431		
55S7	2085	55Si8	56Si7		
55 S 7	2090				
60SC6		60SiCr8	60SiCr8		
Y100C6			100Cr6		
	2092	105WCR 5			
100C3		107CrV3KU			
		35 cRmO 8 KU			
34 CD 4	2234	35CrMo4	34CrMo4	SCM435TK	
105WC13	2140	10WCr6	105WCr5		ChWG
8 MO 8	2140	10WCr6	105WCr5	SKS31	
	2710	45 WCrV8 KU	45WCrSi8		5ChW25F
55WC20	2710	58WCr9KU			
55NCDV7			F.520.S	SKT4	5ChNM
55 NCV 6	2550		f-528		
90 MV8					
100 C 6	2258	100Cr6	F.1310 - 100 Cr 6	SUJ2	SchCh15
45 S 7; Y 46 7; 46 Si 7			F. 1451 - 46 Si 7		
51 S 7; 51 Si 7	2090	48 Si 7; 50 Si 7	F.1450-50 Si 7		
55 S 7	2085; 2090	55 Si 7	F.1440 - 56 Si 7		55S2

MATERIAL GROUPS**According to VDI 3323 Standard**

	 USA	 GERMANY		 Great Britain
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS EN
6	9260	1.5027	60Si7	251 A 60; 251 H 60
6	9260 H	1.5028	65Si7	
6		1.5120	38 MnSi 4	
6	A 204 Gr.A; 4017	1.5415	16Mo3; 15 Mo 3	1503-243 B
6	4419	1.5419	20Mo4	1503-243-430
6	A 350-LF 5	1.5622	14Ni6	
6	3415	1.5732	1 NiCr10	
6	3310; 3314	1.5752	14NiCr14	655M13 36A
6		1.6587	17CrNiMo6	820A16
6		1.6657	14NiCrMo134	
6	5015	1.7015	15 Cr 3	523 M 15
6	5132	1.7033	34Cr4	530A32 18B
6	5140	1.7035	41C r4	530M40 18
6	5140	1.7045	42Cr41	530 A 40
6	5115	1.7131	16MnCr5	527 M 17
6		1.7139	16MnCr5	
6	5155	1.7176	55Cr3	527 A 60 48
6	4135; 4137	1.7220	34CrMo4	708 Aa 37
6	4142	1.7223	41CrMo4	
6	4140	1.7225	42CrMo4	708 M 0
6		1.7228	55NiCrMoV6G	823M30 33
6		1.7262	15CrMo5	
6		1.7321	20 mOcR 4	
6	ASTM A182 F12	1.7335	13CrMo4 4	1501-620Gr27
6	A 182-F11; A 182-F12	1.7335	13 CrMo 4 4	1 501 620 Gr. 27
6	ASTM A 182 F22	1.7380	10CrMo9 10	1501-622gR31; 1501-622gR45
6	A182 F22	1.7380	10 CrMo 9 10	1501-622
6		1.7715	14MoV6 3	1503-660-440

 France AFNOR	 Sweden SS	 Italy UNI	 Spain UNE	 Japan JIS	 Russia GOST
60 S 7		60 Si 7	F. 1441 - 60 Si 7		60S2
60 S 7				50 P 7; SUP 6	
15 D 3	2912	16Mo3 KG; 16Mo3KW	F. 2601 - 16 Mo 3		
	2512	G 20 Mo 5; G 22 Mo5		SCPH 11	
16N6		14 Ni 6 KG; 14 Ni 6 KT	F.2641 - 15 Ni 6		
14 NC 11		16NiCr11	15NiCr11	SNC415(H)	
12NC15				SNC815(H)	
18NCD6			14NiCrMo13		
			14NiCrMo131		
12 C 3				SCr415(H)	15Ch
32C4		34Cr4(KB)	35Cr4	SCr430(H)	35Ch
42C4		41Cr4	42Cr4	SCr440(H)	
42 C 4 TS	2245	41Cr4	42Cr4	SCr440	
16 MC 5	2511	16MnCr5	16MnCr5		
	2127				
55 C 3	2253			SUP9(A)	50ChGA
35 CD 4	2234				35ChM
		41CrMo4	42CrMo4	SNB 22-1	40ChFA
42 CD 4	2244				
	2512	653M31			
12 CD 4	2216		12CrMo4		
	2625				
		14CrMo4 5	14CrMo45		
15 CD 4.5	2216		12CrMo4	SCM415(H)	12ChM; 15ChM
12 CD 9.10	2218	12CrMo9, 12CrMo10	TU.H		
			13MoCrV6		

MATERIAL GROUPS

According to VDI 3323 Standard

	 USA	 GERMANY		 Great Britain	
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS	EN
6	A355A	1.8509	41CrAlMo 7	905 M 39	41B
7	A570.36	1.0038	S235JRG2 (Fe 360 B); RSt 37-2	Fe 360 B FU; 1449 27/23 CR; 4360- 40 B	
7	3135	1.5710	36NiCr6	640A35	111A
7		1.5755	31 NiCr 14	653 M 31	
7	8620	1.6523	2 NiCrMo2	805M20	362
7	8740	1.6546	40 NiCrMo 22	311-Tyre 7	
7	4340	1.6565	40NiCrMo6	817 M 40	24
7	4130	1.7218	25CrMo4	CDS 110	
7		1.7733	24 CrMoV 5 5		
7		1.7755	GS-45 CrMOV 10 4		
7		1.8070	21 CrMoV 5 11		
8	C 45 W	1.173	C 45 W3		
8	4142	1.2332	47 CrMo 4	708 M 40	19A
8	A128 (A)	1.3401	G-X120 Mn 12		
8	3435	1.5736	36 NiCr 10		
8	9840	1.6511	36CrNiMo4	816M40	110
8		1.7361	32 CeMo12	722 M 24	40B
8	6150	1.8159	50 CrV 4	735 A 50	47
8		1.8161	58 CrV 4		
8		1.8515	32 CrMo 12	722 M 24	40B
8		1.8523	39CrMoV13 9	897M39	40C
9		1.4882	X 50 CrMnNiNbN 21 9		
9		1.5864	35 niCr 18		
9			31 NiCrMo 13 4	830 m 31	
10	A 619	1.0347	DCO3; RRSt; RRSt 13	1449 3 CR; 1449 2 CR	
10	M 1015; M 1016; M 1017	1.0401	C15	080 M 15; 080 M 15; 1449 17 CS	
10		1.0723	15 S22; 15 S 20	210 A 15; 210 M 15	

					
France AFNOR	Sweden SS	Italy UNI	Spain UNE	Japan JIS	Russia GOST
40 CAD 6.12	2940	41CrAlMo7	41CrAlMo7		
E 24-2NE	1312	Fe 360 B FN	AE 235 B FN; AE 235 B FU; Fe 360 B FN; Fe 360 B FU		St3ps; St3sp
35NC6				SNC236	
18 NC 13					
20 NCD 2	2506	20NiCrMo2	20NiCrMo2	SNCM220(H)	20ChGNM
		40NiCrMo2(KB)	40NiCrMo2	SNCM240	38ChGNM
35 NCD 6	2541	35NiCrMo6(KB)		SNCM 447	38Ch2N2MA
25 CD 4	2225	25CrMo4(KB)	55Cr3	SCM420; SCM430	20ChM; 30ChM
20 CDV 6		21 CrMoV 5 11			
		35 NiCr 9			
XC 48					
42 CD 4	2244	42CrMo4	42CrMo4	SCM (440)	
Z 120 M 12	2183	GX120Mn12	F. 8251-AM-X120Mn12	SCMnH 1; SCMn H 11	110G13L
30 NC 11					
40NCD3		36nlcRm04(KB)	35NiCrMo4	SUP10	40ChN2MA
30 CD 12	2240	30CrMo12	F.124.A		
50CrV4	2230	50CrV4	51CrV4		50ChGFA
30 CD 12	2240	32CrMo12	F.124.A		
		36CrMoV12			
Z 50 CMNNb 21.09					
	2534		f-1270		
E		Fep 02	AP 02		08JU
AF 37 C12; XC 18	1350	C15; C16; 1 C 15	F.111	S 15 C	
	1922		F.210.F	SUM 32	

ISCAR MATERIAL GROUPS

According to VDI 3323 Standard

	 USA	 GERMANY		 Great Britain
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS EN
10	D 3	1.2080	X 210 Cr 12	BD 3
10	420	1.2083	X 42 Cr 13	
10		1.2085	X 33 CrS 16	
10		1.2162	21 MnCr 5	
10	L2	1.2210	115 Cr V3	
10		1.2311	40 CrMnMo7	
10	P20+S	1.2312	40CrMnMoS 8.6	
10		1.2316	X36CrMo17	X38CrMo16
10	H 11	1.2343	x 38 CrMoV 5 1	BH 11
10		1.234	X 38 CrMoV 5 1	
10	H 13	1.2344	X 40 CrMoV 5 1	BH 13
10	A 2	1.2363	X100 CrMoV 5 1	BA 2
10		1.236	X 100 CrMo V5-1	
10	D 2	1.2379	X 155 CrVMo 12 1	BD2
10		1.238	X 155 CrVMo 12 1	
10	HNV3	1.2379	X210Cr12G	BD2
10	D 4 (D 6)	1.2436	X 210 CrW 12	BD6
10		1.244	X 210 CrW 12	
10	O1	1.251	100 MnCrW 4	B0 1
10	H 21	1.2581	X 30 WCrV 9 3	BH 21
10		1.2601	X 165 CrMoV 12	
10	H 12	1.2606	X 37 CrMoW 5 1	BH 12
10		1.277	X 45 NiCrMo 4	
10	O2	1.284	90 MnCrV 8	B0 2
10	D3	1.3343	S 6-5-2	BM2
10	ASTM A353	1.5662	X8Ni9	1501-509; 1501-510
10	ASM A353	1.5662	X8Ni9	502-650
10	2517	1.568	12Ni19	12Ni19
10	2515	1.5680	12 Ni 19	
10		1.713	16 MnCr 5	
10		1.276	X 19 NiCrMo 4	
11		1.3202	S 12-1-4-5	BT 15

					
France AFNOR	Sweden SS	Italy UNI	Spain UNE	Japan JIS	Russia GOST
Z 200 C 12					
Z40 C14	2314			SUS 420 J 2	
Z35V CD 17.S					
20 MC 5					
100 C3		107 CrV3 KU	F.520 L		
40 CMD 8		35 cRmO 8 KU			
40CMD8S					
Z 38 CDV 5		X 37 CrMoV 5 1 KU			4Ch5MFS
Z 38 CDV 5		X 37 CrMoV 51 KU			
Z 40 CDV 5	2242	X40CrMoV511KU	F-5318	SKD61	4Ch5MF1S
Z 100 CDV 5	2260	X100CrMoV51KU	F-5227	SKD12	
Z 160 CDV 12	2310	X165CrMoW12KU	X160CrMoW12KU	SKD11	
Z 160 CDV 12		X 155 CrMo 12 1 KU			
Z160CDV12	2736				
Z 200 CD 12	2312	X215CrW 12 1 KU	F-5213		
90 MnWRrV5		95MnWCr 5 KU	95 MnCrW 5		
Z 30 WCV 9		X30WCrV 9 3 KU	F-526	SKD5	3Ch2W8F
	2310				
Z 35 CWDV 5		X 35 CrMoW 05 KU	F.537		5ChNM
45 NCD 16		40 NiCrMoV 8 KU			
90 MV 8		90 MnVCr 8 KU			
Z200C12	2715	X210Cr13KU	X210Cr12	SUH3	R6M5
		14 Ni 6 KG; 14 Ni 6 KT	XBNiO9		
9 Ni		X10Ni9	F-2645	SL9N60 ⁽⁵³⁾	
Z18N5					
Z 18 N 5					
16 MC 5					
		HS 12-1-5-5	12-1-5-5		

ISCAR MATERIAL GROUPS

According to VDI 3323 Standard

	 USA	 GERMANY		 Great Britain
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS EN
11		1.3207	S 10-4-3-10	BT42
11	T 15	1.3243	S 6-5-2-5	
11		1.3246	S 7-4-2-5	
11		1.3247	S 2-10-1-8	BM 42
11	M 42	1.3249	S 2-9-2-8	BM 34
11	T 4	1.3255	S 18-1-2-5	BT 4
11	M 2	1.3343	S6-5-2	BM2
11	M 7	1.3348	S2-9-2	
11	T 1	1.3355	S 18-0-1	BT 1
11	HNV 3	1.4718	X45CrSi 9 3	401S45 52
11	422	1.4935	x20 CrMoWV 12 1	
12	403	1.4000	X6Cr13	403 S 17
12		1.4001	X6Cr14	
12	(410S)	1.4001	X7 Cr 13	(403 S 7)
12	405	1.4002	X6CrA12	405S17
12	405	1.4002	X6 CrAl 13	405 S 17
12	416	1.4005	X12CrS 13	416 S 21
12	410; CA-15	1.4006	(G-)X10 Cr 13	410S21 56A
12	430	1.4016	X8Cr17	Z8C17
12	430	1.4016	X6 Cr 17	430 S 15 60
12		1.4027	G-X20Cr14	420C29
12	420	1.4028	X30 Cr 13	420 S 45
12		1.4086	G-X120Cr29	452C11
12	430 F	1.4104	X12CrMoS17	420 S 37
12	440B	1.4112	X90 CrMoV 18	
12	434	1.4113	X6CrMo 17	434 S 17
12		1.4340	G-X40CrNi27 4	
12	S31500	1.4417	X2CrNiMoSi19 5	
12	S31500	1.4417	X2 CrNoMoSi 18 5 3	

					
Z130WKCDV					
KCV 06-05-05-04-02	2723	HS 6-5-2-5	6-5-2-5	SKH55	R6M5K5
Z110 WKCDV 07-05-04	7-4-2-5	HS 7-4-2-5	M 35		
Z110 DKCWV 09-08-04	2-10-1-8	HS 2-9-1-8	M 41		
			2-9-2-8		R6M5
Z 80 WKCV 18-05-04-0					
Z 85 WDCV	2722	HS 6 5 2	F-5604	SKH 51	
Z 100 DCWV 09-04-02-	2782	HS 2 9 2	F-5607		
Z 80 WCV 18-4-01					R18
Z45CS9		X45CrSi8	F322	SUH1	40Ch9S2
Z 6 C 13	2301	X6Cr13	F.3110	SUS403	08Ch13
			F8401		08Ch13
Z 8 C 13	2301				08Ch13
Z8CA12		X6CrAl13			
Z6CA13	2302	X6CrAl13			
Z11 CF 13	2380	X12 CrSC13	F-3411	SUS 416	
Z10 C 13	2302	X12Cr13	F.3401	SUS410	12Ch13
430S15	2320	X8Cr17	F.3113		12Ch17
Z 8 C 17	2320	X8Cr17	F3113	SUS430	12Ch17
Z20C13M					20Ch13L
Z 30 C 13	2304				20Ch13
Z 10 CF 17	2383	X10CrS17	F.3117	SUS430F	
Z 8 CD 17.01	2325	X8CrMo17		SUS434	
	2376				
	2376				

ISCAR MATERIAL GROUPS

According to VDI 3323 Standard

	 USA	 GERMANY		 Great Britain	
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS	EN
12		1.4418	X4 CrNiMo16 5		
12	XM 8; 430 Ti; 439	1.4510			
12	430tl	1.4510	X6 CrTi 17		
12		1.4511	X 6 CrNb 17		
12	409	1.4512	X 6 CrTi 12; (X2CrTi12)	LW 19; 409 S 19	
12		1.4720	X20CrMo13		
12	405	1.4724	X10CrA113	403S17	
12	430	1.4742	X10CrA118	439S15	60
12	HNV6	1.4747	X80CrNiSi20	443S65	59
12	446	1.4749	x18 cRn 28		
12	446	1.4762	X10CrA124		
12	EV 8	1.4871	X 53 CrMnNiN 21 9	349 S 54	
12	302		x12 CrNi 18 9	302 S 31	
12	429		X10 CrNi 15		
13	420	1.4021	X20Cr13	420S37	
13	420	1.4031	X40 Cr 13		
13		1.4034	X46Cr13	420 S 45	
13	431	1.4057	X20CrNi172	431 S 29	57
13	CA6-NM	1.4313	G-X4 CrNi 13 4	425 C 11	
13		1.4544		S. 524; S. 526	
13	348	1.4546	X5CrNiNb 18-10	347 S 31; 2 S. 130; 2 S. 143; 2 S. 144; 2 S. 145; S.525; S.527	
13		1.4922	x20cRmV12-1		
13		1.4923	X22 CrMoV12 1		
14	304	1.4301	X 5 CrNi 18 9	304 S 15	
14	303	1.4305	X10 CrNiS 18 9	303 S 21	58M
14	304L	1.4306	X2CrNi18 9	304S12	
14	304L	1.4306	X2 CrNi 18 10	304 S 11	
14	CF-8	1.4308	X6 CrNi 18 9	304 C 15	58E
14	301	1.4310	X12CrN i17 7	301 S 21	
14	304 LN	1.4311	X2 CrNiN 18 10	304 S 62	
14		1.4312	G-X10CrNi18 8	302C25	
14	305	1.4312	X8 CrNi 18 12	305 s 19	

France AFNOR	Sweden SS	Italy UNI	Spain UNE	Japan JIS	Russia GOST
Z6CND16-04-01	2387				
Z 4 CT 17		X 6 CrTi 17	F.3115 -X 5 CrTi 17	SUS 430 LX	08 Ch17T
Z 4 CT 17					08Ch17T
Z 4 CNb 17		X 6 CrNb 17	F.3122-X 5 CrNb 17	SUS 430 LK	
Z 3 CT 12		X 6 CrTi 12		SUH 409	
Z10C13		X10CrA112	F.311		10Ch13SJU
Z10CAS18		X8Cr17	F.3113	SUS430	15Ch13SJU
Z80CSN20.02		X80CrSiNi20	F.320B	SUH4	
Z10CAS24	2322	X16Cr26		SUH446	
Z 52 CMN 21.09		X53CrMnNiN21 9		SUH35, SUH36	55Ch20G9AN4
Z 10 CN 18-09	2330				
Z 20 C 13	2303	14210			20Ch13
Z 40 C 14	2304				40Ch13
Z40 C 14		X40Cr14	F.3405	SUS420J2	
Z 15 CN 16.02	2321	X16CrNi16	F.3427	SUS431	20Ch17N2
Z 4 CND 13-04 M	2385	(G)X6CrNi304		SCS5	
		X 6 CrNiTi 18 11			08Ch 18N12T
		X 6 CrNiNb 18 11			
	2317	x20cRmOnl 12 01			
Z 5 CN 18.09	2332; 2333				08Ch18N10
Z 8 CNF 18-09	2346	X10CrNiS18.09	F.3508	SUS303	30Ch18N11
Z2CrNi18 10	2352	x2cRnl18 11	F.3503	SCS19	
Z 3 CN 19-11	2352	X2CrNi18 11			
Z 6 CN 18-10 M	2333			SUS304L	
Z 12 CN 17.07	2331	X2CrNi18 07	F.3517		
Z 2 CN18.10	2371	X2CrNiN18 10		SUS304LN	
Z10CN18.9M					10Ch18N9L
					10Ch18N9L

ISCAR MATERIAL GROUPS

According to VDI 3323 Standard

	 USA	 GERMANY	 Great Britain		
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS	EN
14	304	1.4350	X5CrNi18 9	304S15	58E
14	S32304	1.4362	X2 CrNiN 23 4		
14	202	1.4371	X3 CrMnNiN 188 8 7	284 S 16	
14	316	1.4401	X 5 CrNiMo 17 12 2; (X4 CrNiMo 17 -12-2)	316 S 13; 316 S 17; 316 S 19; 316 S 31; 316 S 33	
14	316L	1.4404	X2 CrNiMo 17 13 2; (X2 CrNiMo 17-12-2); GX 2 CrNiMoN 18-10	316 S 11; 316 S 13; 316 S 14; 316 S 31; 316 S 42; S.537; 316 C 12; T.75; S. 161	
14	316LN	1.4406	X2 CrNiMoN 17 12 2; (X2CrNiMoN 18-10)	316 S 61; 316 S 63	
14	CF-8M	1.4408	GX 5 CrNiMoN 7 12 2; G-X 6 CrNiMo 18 10	316 C 16 (LT 196); ANC 4 B	
14		1.4410	G-X10CrNiMo18 9		
14	316 Ln	1.4429	X2 CrNiMo 17 -13-3	316 S 62	
14	316L	1.4435	X2 CrNiMo18 14 3	316 S 11; 316 S 13; 316 S 14; 316 S 31; LW 22; LWCF 22	
14	316	1.4436	X 5 CrNiMo 17 13 3; (X4CRNIMO 17-13-3)	316 S 19; 316 S 31; 316 S 33; LW 23; LWCF 23	
14	317L	1.4438	X2 CrNiMo 18 16 4; (X2CrNiMo 18-15-4)	317 S 12	
14	(s31726)	1.4439	X2 CrNiMoN 17 13 5		
14		1.444	X 2 CrNiMo 18 13		
14	317	1.4449	X5 CrNiMo 17 13 3	317 S 16	
14	329	1.4460	X 4 CrNiMo 27 5 2; (X3CrNiMo27-5-2)		
14	329	1.4460	X8CrNiMo27 5		

 France AFNOR	 Sweden SS	 Italy UNI	 Spain UNE	 Japan JIS	 Russia GOST
Z6CN18.09	2332	X5CrNi18 10	F.3551	SUS304	
Z 2 CN 23-04 AZ	2327				
Z 8 CMN 18- 08-05					
Z 3 CND 17 -11-01; Z 6 CND 17-11; Z 6 CND 17-11-02; Z 7 CND 17-11-02; Z 7 CND 17-12-02	2347	X 5 CrNiMo 17 12	F.3534-X 5 CrNiMo 17 12 2	SUS 316	
Z 2 CND 17-12; Z 2 CND 18-13; Z 3 CND 17-11-02; Z 3 CND 17-12-02 FF; Z 3 CND 18-12-03; Z 3 CND 19.10 M	2348	X 2 CrNiMo 17 12; G-X 2 CrNiMo 19 11	F.3533 - X 2 CrNiMo 17 13 2; F.3537 - X 2 CrNiMo 17 13 3	SUS 316 L	
Z2 CND 17-12 AZ		X 2 CrNiMoN 17 12	F.3542-X 2 CrNiMoN 17 12 2	SUS316LN	07 Ch 18N
	2343		F.8414-AM-X 7 CrNiMo 20 10	SCS 14	10G2S2MSL
Z5CND20.12M	2328				
Z 2 CND 17-13 Az	2375	X 2 CrNiMoN 17 13	F.3543-X 2 CrNiMoN 17 13 3	SUS 316 LN	
Z 3 CND 17-12-03; Z 3 CND 18-14-03	2375	X2CrNiMoN 17 13	F.3533-X 2 CrNiMo 17 13 2	SUS 316 L	O3 Ch 17N14M3
Z 6 CND 18-12-03; Z 7 CND 18-12-03	2343	X 5 CrNiMo 117 13; X 8 cRnlMo 17 13	F.3543-X 5 CrNiMo 17 12 2 F.3538-X 5 CrNiMo 17 13 3	SUS 316	
Z 2 CND 19-15-04; z 3 cnd 19-15-04	2367	X2CrNiMo18 16	f.3539-x 2 cRnlMo 18 16 4	SUS317L	
Z 3 CND 18-14-06 AZ					
		X 5 CrNiMo 18 15		SUS 317	
(Z 3 CND 25-07 Az); Z 5 CND 27-05 Az	2324		F.3309-X 8 CrNiMo 17 12 2; F.3552-X 8 CrNiMo 18 16 4	SUS 329 J 1	
	2324				

ISCAR MATERIAL GROUPS**According to VDI 3323 Standard**

Mtl. No.	AISI/SAE	Werkstoff	DIN	Great Britain	
				BS	EN
14		1.4462	X2CrNiMoN22 5 3	318 S 13	
14		1.4500	G-X7NiCrMoCuNb25 20		
14	17-7PH	1.4504		316S111	
14	443 444	1.4521	X2CrMoTi18-2		
14	UNS N 08904	1.4539	X1NiCrMoCuN25-20-5		
14	CN-7M	1.4539	(G-)X1 NiCrMoCu 25 20 5		
14	321	1.4541	Z 6 CrNiTi 18-10	321 S 31; 321 S 51 (1010; 1105); LW 24; LWCF 24	
14	630	1.4542	X5 CrNiCuNb 17 4; (X5 CrNiChNb 16-4)		
14	15-5PH	1.4545	Z7 CNU15.05		
14	S31254	1.4547	X1 CrNiMoN 20 18 7		
14	347	1.4550	X6 CrNiNb 18 10	347 S 17	58F
14		1.4552	G-X7CrNiNb18 9		
14	17-7PH	1.4568		316S111	
14	316tTi	1.4571	X6 CrNiMoTi 17 12 2	320 S 31	
14	316 Ti	1.4571	x 6 CrNiMoTi 17 12 2	320 S 31	58J
14		1.4581	G-X 5 CrNiMoNb	318 C 17	
14	318	1.4583	X 10CrNiMoNb 18 12	303 S 21	
14		1.4585	G-X7CrNiMoCuNb18 18		
14		1.4821	X20CrNiSi25 4		
14		1.4823	G-X40CrNiSi27 4		
14	309	1.4828	X15CrNiSi20 12	309 S 24	58C
14	309S	1.4833	X6 CrNi 22 13	309 S 13	
14	310 S	1.4845	X12 CrNi 25 21	310S24	
14	321	1.4878	X6 CrNiTi 18 9	32 1 S 20	58B

 France AFNOR	 Sweden SS	 Italy UNI	 Spain UNE	 Japan JIS	 Russia GOST
Z 3 CND 22-05 Az; (Z 2 CND 24 -08 Az); (Z 3 CND 25-06-03 Az)	2377			SUS 329 J3L	
23NCDU25.20M					
		Z8CNA17-07	X2CrNiMo1712		
	2326		F.3123-X 2 CrMoTiNb 18 2	SUS 444	
Z 2 NCDU 25-20	2562				
Z1 NCDU 25-02 M	2564				
Z 6 CNT 18-10	2337	X 6 CrNiTi 18 11	F.3523 - X 6 CrNiTi 18 10	SUS 321	06Ch18N10T; 08Ch18N10T; 09Ch18N10T; 12Ch18N10T
Z 7 CNU 15-05; Z 7 CNU 17-04				SCS 24; SUS 630	
	2378				
Z 6 CNNb 18.10	2338	X6CrNiNb18 11	F.3552	SUS347	08Ch18N12B
Z4CNNb19.10M					
		Z8CNA17-07	X2CrNiMo1712		09Ch17NJu1
Z 6 CNDT 17-12002	2350				10Ch17N13M2T
Z 6 NDT 17.12	2350	X6CrNiMoTi17 12	F.3535		10Ch17N13M2T
Z 4 CNDNb 18.12 M					
Z15CNS20.12		x15cRnlsI2 12			
		X6CrNiMoTi17 12			
Z20CNS25.04					
Z15CNS20.12			F.8414	SCS17	20Ch20N14S2
Z 15 CN 24-13					
Z 12 CN 25-20	2361	X6CrNi25 20	F.331	SUH310	20Ch23N18
Z 6 CNT 18-12 (B)	2337	X6CrNiTi18 11	F.3553	SUS321	

ISCAR MATERIAL GROUPS

According to VDI 3323 Standard

	 USA	 GERMANY	 Great Britain		
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS	EN
14	Ss30415	1.4891	X5 CrNiNb 18 10		
14	S30815	1.4893	X8 CrNiNb 11		
14	304H	1.4948	X6 CrNi 18 11	304 S 51	
14	660	1.4980	X5 NiCrTi 25 15		
14			X5 NiCrN 35 25		
14	S31753		X2 CrNiMoN 18 13 4		
14			X2 CrNiMoN 25 22 7		
15	CLASS20	0.6010	GG10		
15	A48-20B	0.6010	GG-10		
15	NO 25 B	0.6015	GG 15	Grade 150	
15	CLASS25	0.6015	GG15	GRADE150	
15	A48 25 B	0.6015	GG 15	Grade 150	
15	A48-30B	0.6020	GG-20	Grade 220	
15	NO 30 B	0.6020	GG 20	Grade 220	
15	A436 Type 2	0.6660	GGL-NiCr202	L-NiCuCr202	
15	60-40-18	0.7040	GGG 40	SNG 420/12	
15	No 20 B		GG 10		
16	CLASS30	0.6020	GG20	GRADE220	
16	A48-40 B	0.6025	EN- GJL-250 (GG25)	Grade260	
16	CLASS45	0.6030	GG30	GRADE300	
16	A48-45 B	0.6030		Grade 300	
16	A48-50	0.6035	GG-35	GRADE 350	
16	A48-60 B	0.6040	GG40	GRADE400	
16		1.4829	X 12 CrNi 22 12		
16					
16					
17		0.7033	GGG-35.3	350/22 L 40	
17	60/40/18	0.7043	GGG-40.3	370/7	
17	80-55-06	0.7050	EN- GJS-800-7 (GGG50)	SNG500/7	
17	65-45-12	0.7050	GGG-50	SNG 500/7	
17		0.7652	GGG-NiMn 13 7	S-NiMn 137	
17	A43D2	0.7660	GGG-NiCr 20 2	Grade S6	

France AFNOR	Sweden SS	Italy UNI	Spain UNE	Japan JIS	Russia GOST
	2372				
	2368				
Z 5 CN 18-09	2333				
Zz 8 nctv 25-15 b ff	2570				
Ft10D	110	G10			SCh10
FT 10 D	0110-00				SCh10
FT 15 D	0115-00	G 15	FG 15	FC150	SCh15
Ft15D	115	G 15	FG 15		SCh15
Ft 15 D	01 15-00	G14	FG15		SCh15
Ft 20 D	0120-00				SCh20
Ft 20 D	120	G 20		FC200	SCh20
L-NC 202	0523-00				
FCS 400-12	0717-02	GS 370-17	FGE 38-17	FCD400	VCh42-12
Ft 10 D	110			FC100	
Ft20D	120	G 20	FG 20		
Ft 25 D	125	G 25	FG 25	FC250	VCh60-2
Ft30D	130	G 30	FG 30	FC300	SCh20
Ft 30 D	01 30-00				SCh30
Ft35D	135	G 35	FG 35	FC350	SCh30
Ft 40 D	140				SCh40
					SCh25
FGS 370/17	0717-15				VCh42-12
FGS 370/17	0717-15				VCh50-2
FGS 500/7	0727-02	GGG 50		FCD500	VCh50-2
FGS 500-7	0727-02				
S-Mn 137	0772-00				
S-NC 202	0776-00				

ISCAR MATERIAL GROUPS

According to VDI 3323 Standard

	 USA	 GERMANY	 Great Britain		
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS	EN
17			GGG 40.3	SNG 370/17	
18		0.7060	GGG60	SNG600/3	
18	80/55/06	0.7060	GGG-60	600/3	
18	100/70/03	0.7070	GGG-70	SNG700/2	
18	A48 40 B				
19		0.8055	GTW55		
19	32510	0.8135	GTS-35-10	B 340/12	
19	A47-32510	0.8135	GTS-35-10	B 340/2	
19	A220-40010	0.8145	GTS-45-06	P 440/7	
19			GTS-35	B 340/12	
19				8 290/6	
19	32510		GTS-35	B340/12	
20		0.8035	GTM-35	W340/3	
20		0.8040	GTW-40	W410/4	
20		0.8045			
20		0.8065	GTMW-65		
20	A220-50005	0.8155	GTS-55-04	P 510/4	
20	50005	0.8155	GTS-55-04	P510/4	
20	70003	0.8165	GTS-65-02	P 570/3	
20	90001	0.8170	GTS-70-02	P 690/2	
20	A220-90001	0.8170	GTS-70-02		
20	1022; 1518	1.1133	20Mn5	120 M 19	
20	400 10		GTS-45	P440/7	
20	70003		GTS-65	P 570/3	
21	Al99	3.0205			
21	1000	3.0255	Al99.5	L31; L34; L36	
21		3.3315	AlMg1		
22		3.1325	AlCuMg 1		
22		3.1655	AlCuSiPb		
22		3.2315	AlMgSi1		
22	7050	3.4345	AlZnMgCuO,5	L 86	
22		3.437	AlZnMgCu 1,5		
23		3.2381	G-AlSi 10 Mg		
23		3.2382	GD-AlSi10Mg		

					
France AFNOR	Sweden SS	Italy UNI	Spain UNE	Japan JIS	Russia GOST
FGS 370-17	0717-12			FC250	
FGS600-3	07 32-03	GGG 60	GGG 60		
FGS 600/3	0727-03			FCD600	
FGS 700-2	07 37-01	GGG 70	GGG 70	FCD700	
			GTW 55		
MN35-10	810		GTS 35		KCh35-10
Mn 35-10	0815-00				KCh35-10
Mn 450-6	0852-00	GMN 45		FCMW370	
	0810-00				
MN 32-8	814			AC4A	
MN 35-10	08 15			FCMW330	
MB35-7	852		GTM 35		
MB40-10		GMB40	GTM 40		
		GMB45	GTM 45		KCh55-4
			GTW 65		KCh55-4
Mn 550-4	0854-00				KCh60-3
MP 50-5	854	GMN 55		FCMP490	KCh70-2
Mn 650-3	0856-00	GMN 65		FCMP590	KCh70-2
Mn 700-2	0862-00	GMN 70		FCMP690	KCh70-2
Mn 700-2	0864-00				20G
20 M 5	2132	G 22 Mn 3; 20 Mn 7	F.1515-20 Mn 6	SMnC 420	
	08 52				
MP 60-3	858			FCMP540	AD0
A59050C					D1
					AD35
					AK9
AZ 4 GU/9051		811-04			AK12

ISCAR MATERIAL GROUPS

According to VDI 3323 Standard

	 USA	 GERMANY	 Great Britain		
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS	EN
23	A360.2	3.2383	G-AlSi0Mg(Cu)	LM9	
23		3.2581	G-AlSi12		
23		3.3561	G-AlMg 5		
23	ZE 41	3.5101	G-MgZn4sE1Zr1	MAG 5	
23	EZ 33	3.5103	MgSE3Zn27r1	MAG 6	
23	AZ 81	3.5812	G-MgAl8Zn1	NMAG 1	
23	AZ 91	3.5912	G-MgAl9Zn1	MAG 7	
23	A356-72			2789; 1973	
23	356,1			LM25	
23	A413.2		G-AlSi12	LM 6	
23	A413.1		G-AlSi 12 (Cu)	LM 20	
23	A413.0		GD-AlSi12		
23	A380.1		GD-AlSi8Cu3	LM24	
24		2.1871	G-AlCu 4 TiMg		
24		3.1754	G-AlCu5Ni1,5		
24		3.2163	G-AlSi9Cu3		
24	4218 B	3.2371	G-AlSi 7 Mg		
24	SC64D	3.2373	G-AlSi9MGWA		
24		3.2373	G-AlSi 9 Mg		
24	QE 22	3.5106	G-MgAg3SE2Zr1	mag 12	
24	GD-AISI12		G-ALMG5	LM5	
26	C93200	2.1090	G-CuSn 7 5 pb		
26	c 83600	2.1096	G-CuSn5ZnPb	LG 2	
26	C 83600	2.1098	G-CuSn 2 Znpb		
26	C23000	2.1182	G-CuPb15Sn	LB1	
26	C 93800	2.1182	G-CuPb15Sn		
27		2.0240	CuZn 15		
27	C27200	2.0321	CuZn 37	cz 108	
27	C27700	2.0321	CuZn 37	cz 108	
27		2.0590	G-CuZn40Fe		
27	C 86500	2.0592	G-CuZn 35 Al 1	U-Z 36 N 3	
27	C 86200	2.0596	G-CuZn 34 Al 2	HTB 1	
27	C 18200	2.1293	CuCrZr	CC 102	

					
France AFNOR	Sweden SS	Italy UNI	Spain UNE	Japan JIS	Russia GOST
	4253				
G-TR3Z2					
NF A32-201					
	4244			A5052	AK7
	4261				
	4260			ADC12	AK12
	4247			A6061	
	4250			A7075	
					VAL 8
					AK8
A-S7G	4251			C4BS	AK9
A-SU12	4252				
U-E 7 Z 5 pb 4					
U-pb 15 E 8					
Uu-PB 15e 8					
CuZn 36, CuZn 37		C 2700			L 63
CuZn 36, CuZn 37		C2720			L 63
HTB 1					
U-Z 36 N 3					L Ts23AD; ZMts
U-Cr 0.8 Zr					

ISCAR MATERIAL GROUPS

According to VDI 3323 Standard

	 USA	 GERMANY	 Great Britain		
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS	EN
28		2.0060	E-Cu57		
28		2.0375	CuZn36Pb3		
28	C 63000	2.0966	CuAl 10 Ni 5 Fe 4	Ca 104	
28	B-148-52	2.0975	G-CuAl 10 Ni		
28	c 90700	2.1050	G-CuSn 10	CT1	
28	C 90800	2.1052	G-CuSn 12	pb 2	
28	C 81500	2.1292	G-CuCrF 35	CC1-FF	
28		2.4764	CoCr20W15Ni		
31	N 08800	1.4558	X 2 NiCrAlTi 32 20	NA 15	
31	N 08031	1.4562	X 1 NiCrMoCu 32 28 7		
31	N 08028	1.4563	X 1 NiCrMoCuN 31 27 4		
31	N 08330	1.4864	X 12 NiCrSi 36 16	NA 17	
31	330	1.4864	X12 NiCrSi 36 16	NA 17	
31		1.4865	G-X40NiCrSi38 18	330 C 40	
31		1.4958	X 5 NiCrAlTi 31 20		
31	AMS 5544	2.4668	NiCr19NbMo		
32		1.4977	X 40 CoCrNi 20 20		
33	Monel 400	2.4360	NiCu30Fe	NA 13	
33	5390A	2.4603			
33	Hastelloy C-4	2.4610	NiMo16cR16Ti		
33	Nimonic 75	2.4630	NiCr20Ti	HR 5,203-4	
33		2.4630	NiCr20Ti	HR5,203-4	
33	Inconel 690	2.4642	NiC29Fe		
33	Inconel 625	2.4856	NiCr22Mo9Nb	NA 21	
33	5666	2.4856	NiCr22Mo9Nb		
33	Incoloy 825	2.4858	NiCr21Mo	NA 16	
34	Monel k-500	2.4375	NiCu30 Al	NA 18	
34	4676	2.4375	NiCu30Al	3072-76	
34		2.4631	NiCr20TiAl	Hr40; 601	
34	Inconel 718	2.4668	NiCr19FeNbMo		
34	Inconel 751	2.4694	NiCr16fE7TiAl		
34		2.4955	NiFe25Cr20NbTi		
34	5383	2.4668	NiCr19Fe19NbMo	HR8	
34	5391	2 4670	S-NiCr13A16MoNb	3146-3	

 France AFNOR	 Sweden SS	 Italy UNI	 Spain UNE	 Japan JIS	 Russia GOST
					LS60-2
U-A 10 N					BrAD; N10-4-4
UE 12 P					
Z1NCDU31-27-03	2584				EK 77
Z 12 NCS 35.16					
Z 12 NCS 37.18				SUH330	
		XG50NiCr39 19		SCH15	
NC20K14					
Z 42 CNKDWNb					
NU 30					
NC22FeD					
NC 20 T					
NC20T					
Nnc 30 Fe					
NC 22 FeDNb					
Inconel 625					
NC 21 Fe DU					KhN38VT
NU 30 AT					
NC20TA					KhN77TYuR
NC 19 Fe Nb					
NC19eNB					
NC12AD					

ISCAR MATERIAL GROUPS

According to VDI 3323 Standard

	 USA	 GERMANY	 Great Britain		
Mtl. No.	AISI/SAE	Werkstoff	DIN	BS	EN
34	5660	2.4662	NiFe35Cr14MoTi		
34	5537C	2.4964	CoCr20W15Ni		
34	AMS 5772		C0Cr22W14Ni		
35	Inconel X-750	2.4669	NiCr15Fe7TiAl		
35	Hastelloy B	2.4685	G-NiMo28		
35	Hastelloy C	2.4810	G-NiMo30		
35	AMS 5399	2.4973	NiCr19Co11MoTi		
35		3.7115	TiAl5Sn2		
36	R 50250	3.7025	Ti 1	2 TA 1	
36	R 52250	3.7225	Ti 1 pd	TP 1	
36	AMS 5397	2.4674	NiCo15Cr10MoAlTi		
37		3.7124	TiCu2	2 TA 21-24	
37	R 54620	3.7145	TiAl6Sn2Zr4Mo2Si		
37		3.7165	TiAl6V4	TA 10-13; TA 28	
37		3.7185	TiAl4Mo4Sn2	TA 45-51; TA 57	
37		3.7195	TiAl 3 V 2.5		
37			TiAl4Mo4Sn4Si0.5		
37	AMS R54520		TiAl5Sn2.5	TA14/17	
37	AMS R56400		TiAl6V4	TA10-13/TA28	
37	AMS R56401		TiAl6V4ELI	TA11	
38	W 1	1.1545	C 105 W1	BW 1A	
38	W210	1.1545	C105W1	BW2	
38		1.2762	75 CrMoNiW 6 7		
38	440C	1.4125	X105 CrMo 17		
38		1.6746	32 nlcRmO 14 5	832 M 31	
40	Ni- Hard 2	0.9620	G-X 260 NiCr 4 2	Grade 2 A	
40	Ni- Hard 1	0.9625	G-X 330 Ni Cr 4 2	Grade 2 B	
40	Ni-Hard 4	0.9630	G-X 300 CrNiSi 9 5 2		
40		0.9640	G-X 300 CrMoNi 15 2 1		
40	A 532 III A 25% Cr	0.9650	G-X 260 Cr 27	Grade 3 D	
40	A 532 III A 25% Cr	0.9655	G-X 300 CrNMo 27 1	Grade 3 E	
40	310	1.4841	X15 CrNiSi 25 20	314 S31	
41		0.9635	G-X 300 CrMo 15 3		
41		0.9645	G-X 260 CrMoNi 20 2 1		

 France AFNOR	 Sweden SS	 Italy UNI	 Spain UNE	 Japan JIS	 Russia GOST
ZSNCDT42					
KC20WN					
KC22WN					
NC 15 TNb A					
NC19KDT					VT5-1
					VT1-00
T-A 6 V					VT6
T-A5E					
T-A6V					
Y1 105	1880	C 100 KU	F-5118	SK 3	
Y120	2900	C120KU	CF.515	SUP4	U10A
Z 100 CD 17		X 105 CrMo 17			95Ch18
35 NCD 14					
	0512-00				
	0513-00				
	0466-00				ChWG
					20Ch25N20S2
Z 15 CNS 25-20					

Alphabetical Index

3M AXKT 1304	447
3M AXKT 1304..R-PDRMM	448
3M AXKT-2006	448
3M AXKT 2006..R-PDR	448
A	
ADBH	874
ADCR 1505PDR	441
ADCT 1505PDR-HM	442
ADJ BT	1052
ADJ BT-ER	1028
ADJ C-ER	1002
ADJ DIN69871	1052
ADJ DIN69871-ER	955
ADJ ER NOSE	1051
ADJ HSK A	1052
ADJ HSK A-ER	984
ADJ HYDRO	1050
ADJ ST	1051
ADJ ST-ER	1053
Adjustable Torque Handles	516
ADKR 1505PDR/L-HM	441
ADKT 1505-FF	444
ADKT 1505PDR/L-HM	443
ADKT 1505PDTR-76	444
ADKT 1505PDTR/L-RM	443
ADKT 1505PD-W	445
ADKT 1505..R/L-HM	444
ADKW (CBN)	442
ADKW (PCD)	442
ADM 1505PDR-HS	443
AMT MB-MT	841
AOMT	594
AOMT-Chamfering	611
APCR 1003PDR-P	436

A	APCR 1604	446
	APCT 1003PDR-HM	435
	APK-FE	234
	APKR 1003PDR-HM	436
	APKT 1003PDR-HM	436
	APKT 1003PDTR-76	437
	APKT 1003PDTR/L-RM	437
	APKT 1003..R	438
	APKT 1003R8T-FF	439
	APKT 1003..TR-RM	437
	APKT 1604	445
	APKW 100304 PDR (PCD)	435
B	BBH 30/40	873
	BBH 63	874
	BBH D16	263
	BCM	264
	BCM-M	264
	BCM-MM	257
	BCR	511
	BHC MB	850
	BHD 50 L200	875
	BHD MB	853
	BHEH	874
	BHE MB	857
	BHE MB-H	857
	BHFH	874
	BHF L200	875
	BHF MB16-MB50 Dia. 2.5-108	864
	BHF MB50-MB80 Dia. 77-500	871
	BHF MB-BL	862
	BHR MB	843
	BLANK MB	842
	BLP Endmills	260
	BLPK	262
	BLP-M	261
	BLP Shell Mill	261
	BLR	511
	BT-AD	1027
	BTB-MB	832

B	BT-C#	1026
	BT-CF (CLICKFIT)	1029
	BT-DC-B	1026
	BT-EM (DIN 1835 Form B)	1013
	BT-EM (DIN 1835 Form E)	1015
	BT-EM (Short)	1012
	BT-ER	1006
	BT-ER-CLICKIN	1030
	BT-ER-SHORT	1008
	BT-FC-EM	1014
	BT-FC-ER	1008
	BT-FC-FM	1024
	BT-FC-HYDRO	1012
	BT-FC-MAXIN	1010
	BT-FC-MB	832
	BT-FC-SEM-C	1023
	BT-FC-SRK	1020
	BT-FC-SRKin	1018
	BT-FM	1024
	BT-HYDRO	1010
	BT-HYDRO HD	1011
	BT-MAXIN	1009
	BT-MB	831
	BT-MT	1027
	BT-MT-DRW	1028
	BT-ODP (FLEXFIT)	307, 1030
	BT-SEM	1021
	BT-SEM-C	1022
	BT-SEMC	1025
	BT-SRK	1019
	BT-SRKin	1016
	BT-SRKin-CX	1017
C	CA90 1723-R/L-T490-13	352
	CA90 1928-R/L-PM15	351
	CA90-R/L-LN11/15 Cartridges	351
	CAB M-M (FLEXFIT)	305, 1046
	CAB M-SEM	1046
	CAID	694
	CAOD	694

C	CAORC	694
	CA-SPM	383
	CATM-MB	830
	C#-B4340 (blank)	1003
	CCET-WF	890
	C#-CF4 (CLICKFIT)	994
	CCGT-AF	892
	CCGT-AS	891
	CCGW/CCMT (CBN)	891
	CC MB-ER	838
	CCMT-14	889
	CCMT/CCGT	890
	CCMT/CCGT-SM	889
	CCMT (PCD)	891
	CCMT-PF	889
	CCMT-WG	890
	CDP ER-M	305, 1048
	CDP M-SRK	1047
	C#-EM	994
	C#-EM-E	995
	C#-ER	991
	C#-ER-M	993
	C#-FM	1000
	CH45-MM-PN06	33
	CH45-PN06	33
	CHA	846
	CHAMRING	616
	CHR MB	837
	CHS MB-R	837
	C#-MAXIN	993
	C#-MB	831
	CNHT/MT 07	513
	C#-ODP (FLEXFIT)	307, 1001
	COOLANT SET	225, 1104
	COOLING TUBE C#	1106
	COOLING TUBE HSK-A	1104
	C#-SEM-C	999
	C#-SEMC	1000
	C#-SRKIN	997

C	C#-SRKIN-CX	998
	CW32	875
	CW200	875
D	D3N A-1.5D	550
	D3N A-3D	551
	D3N A-5D	552
	D3N R-1.5D	550
	D3N R-3D	551
	D3N R-5D	552
	DCGT-AS	894
	DCM-3.5D (7.5-20.9 mm)	580
	DCM-3D (7.5-25.9 mm)	579
	DCM-5D (7.5-25.9 mm)	580
	DCM-8D (10-25.9 mm)	581
	DC MB	838
	DCMT-14	892
	DCMT/DCGT	893
	DCMT/DCGT-SM	892
	DCMT-PF	893
	DCN A-1.5D	528
	DCN A-3D	530
	DCN A-5D	535
	DCN A-8D	538
	DCN C-3D	531
	DCN C-5D	536
	DCNM	541
	DCN R-1.5D	529
	DCN R-3D	532
	DCN R-5D	537
	DCN R-8D	539
	DCN R-12D	540
	DCNS-3D	533
	DCNS-5D	534
	DCNT (M8-M24)	613
	DCT (M8-M24)	611
	DDC-E1	687
	DDD-E3	684
	DDD-EC	686
	DDD-EF-FB	686

D	DDD-EF-FT	685
	DDT-E1	688
	DFN A-1.5D-IQ	572
	DFN A-3D-IQ	572
	DFN A-5D-IQ	573
	DFN A-8D-IQ	573
	DGM-V	323
	DGSM-M-JHP	323
	DGSM-MM-JHP	323
	DIN2079-MB	835
	DIN2080-EM	1034
	DIN2080-ER	1033
	DIN2080-FM	1035
	DIN2080-SEM	1035
	DIN2080-SEMC	1036
	DIN69871-AD	953
	DIN69871-C#	953
	DIN69871-CF	956
	DIN69871-EM (DIN 6359-HB)	944
	DIN69871-EM (DIN 6359-HE)	945
	DIN69871-EM (DIN 6359 short)	944
	DIN69871-ER (form ADB)	940
	DIN69871-ER-SHORT	941
	DIN69871-FM	951
	DIN69871-HYDRO	943
	DIN69871-HYDRO HD	944
	DIN69871-MAXIN	942
	DIN69871-MT	954
	DIN69871-MT-DRW	954
	DIN69871-ODP	308, 957
	DIN69871-SEM	949
	DIN69871-SEM-C	950
	DIN69871-SEMC	952
	DIN69871-SRK	946
	DIN69871-SRKin	947
	DIN69871-SRKin-CX	948
	DR-2D-N	588
	DR-3D-N	590
	DR-4D-N	591

D	DR-4D-T	593
	DR-CA	594
	DRG-MF	619
	Drilling Eccenter Sleeves	605, 1053
	Driving Ring-SEMC	1103
	DSC-E1	675
	DSC-EA	676
	DSC-EC	677
	DSC-I1	681
	DSC-IA	683
	DSC-IC	683
	DSD-E0	672
	DSD-E1	672
	DSD-E2/E3	673
	DSD-EC	674
	DSD-EF-FB	675
	DSD-EF-FT	674
	DSD-I1	678
	DSD-IC	680
	DSD-IF-FB	679
	DSD-IF-FT	679
	DST-E1	676
	DST-I1	682
E	E30 / T230	32
	E45 / T245	34
	E45X	34
	E60 / T260	35
	E90AC	32
	E90CN	13
	E90CN-M	12
	E90SO-04	9
	E90SO-MM-04	9
	E90SP	19
	E90X	13
	E90XC	32
	E93CN	265
	E93CN-M	265
	E93CN-MM	266
	EB-A-2	157

E	EB-A2 (economical)	158
	EB-A2(economical-extra long)	159
	EB-A2 (extra long)	165
	EB-A2-H (rib processing)	162
	EB-A2 (long with neck)	164
	EB-A2 (precision stub cut)	166
	EB-A2 (rib processing)	163
	EB-A2 (stub cut length)	158
	EB-A2 (tapered flute & neck)	165
	EB-A-3	159
	EB-A4 (economical-short)	160
	EB-A-4 (medium length)	161
	EB-A-4 (short length)	160
	EBA-B2	152
	EB-E4L-CF	157
	EB-H-CF	156
	EBL-A-4	161
	EBM-A-2	166
	EBRF-T	119
	EC-A-2	122
	EC-A2(economical-extra long)	123
	EC-A2 (economical-medium)	122
	EC-A2 (economical-short)	121
	EC-A2-H (rib processing)	138
	EC-A2 (medium length)	141
	EC-A2-M (rib processing)	139
	EC-A2-R (rib processing)	136
	EC-A3/E3 (economical-medium)	125
	EC-A3/E3 (economical-short)	124
	EC-A-4	133
	EC-A4	142
	EC-A4(economical-extra long)	135
	EC-A4 (economical-medium)	134
	EC-A-4R	134
	ECA-B-2	152
	ECA-B-3	153
	ECA-F-2	153
	ECA-H3-CF	147
	ECA-H3-CF-C	149

E	ECA-H4-CF	149
	ECAP-H3-CF	150
	EC-B-3	129
	EC-B3 (economical-medium)	128
	EC-B3 (economical-short)	125
	EC-B-3R	130
	EC-B-4	131
	EC-B-4R	132
	EC-B4-R	143
	EC-B6	145
	EC-B6-H	146
	ECC-A-2	123
	ECC-A-4	135
	ECC-E-3	127
	EC-D6	145
	ECD-S2	168
	EC-E-3	126
	EC-E3/E7-CE (ceramic)	109
	EC-E4L-CF	114
	EC-E5L-CF	114
	EC-E7/H7-CF	105
	ECF./45	167
	EC-H4L-CFR (relieved neck)	102
	EC-H4M-CF-E	101
	EC-H4M-CFR	102
	EC-H4S-CF	101
	EC-H4XL-CFR (relieved neck)	103
	EC-H5M-CFR	104
	ECH-B-6	143
	EC-H-CF	109
	ECK-H4M-CFR	110
	ECK-H7/9-CFR	111
	ECL-B-4/6	144
	ECP-E3L	117
	ECP-E4L	118
	ECP-H4L-CFR	103
	ECP-H7-CF	107
	ECR-B3-R	151
	ECR-B3-R-C	151

E

ECR-B-L	116
ECR-B-M/ECR-B-M...R	115
ECR-B-MF	117
ECR-B-S	115
ECR-B-X	116
ECR-T-M	119
ECS/ECCS-E-3	124
ECU-E-3	127
ECU-E-3-R	128
ECXL-B-4/6	144
EFF-S	120
EFP-E4,5CF	120
EFS-B44	113
EFS-E44	112
EMH MB	837
ENHT	514
EPNC	154
EPND	155
EPN-F	154
EPX	155
ER	273
ERC-E-3	150
ERF-A/E-3,4,6	118
ER-M	273
ER-ODP	308, 1048
ER-SEAL	1068
ER-SEAL-JET2	1069
ER-SPR	1066
ER-SPR-AA	1067
ER-SRF	1079
ER-SRK	1073
ER-SRK-JET2	1075
ERW	274
ERW-M	275
ESB-A2	167
ESB-A4	167
ETR-A2	121
ETS	330

E	ETS Gear Mill	365
	ETS-LN08	326
	ETS-LN08-M	324
	ETS-LN08-MM	325
	ETS-XN13	330
	EX C# (CAMFIX extension)	1002
	EX-MB	835
	EXTRACTOR SC COLLETS	1105
F	F45E	220
	F45NM	216
	F45ST	220
	F45WG	215
	F86LNX-11	210
	F90	208
	F90AD-SFR	204
	F90LN-FR CA11	381
	F90LN-N11	196
	F90LN-N15	201
	F90SD-12	197
	F90SP-10	191
	F93CN	266
	FCP	546
	FDN	336
	FDN-CALN11	338
	FDN-CALN12	337
	FDN-CALN13	339
	FDN-CALN15	340
	FDN-CAPM15	339
	FDN-CF4	336
	FDN-CM	340
	FDN-LN08	334
	FDN-LN12	335
	FDN-XN13	338
	FF EW	294
	FF EW-CF	295
	FF EW-M	295
	FF EWX	290
	FF EWX-M	291
	FF EWX-MM	291

F	FF FW	299
	FF FWX	296
	FF NM	299
	FFQ4 D-09	300
	FFQ4 D-12	301
	FFQ4 D-17	302
	FFQ4 D-M-09	293
	FFQ4 D-W-09	293
	FFQ4 SOMT 0904	500
	FFQ4 SOMT 1205	500
	FFQ4 SOMT 1706	500
	FF SOF	303
	FFT3 EFM-02	286
	FFT3 EFM-03	287
	FFT3 EFM-MM 02	286
	FFT3 EFM-MM 03	287
	FFT3 TXMT 02	431
	FFT3 WXMT 03	501
	FFV-D-R-VN07	298
	FF VNMT 0706	503
	FF WOMT/WOCT	501
	FFX4 ED	288
	FFX4 ED-M	288
	FFX4 ED-MM	289
	FFX4 FD	289
	FFX4 XNMU	503
	FIN LNAT 1607PN-R	475
	FIN LNK-BT	235
	FIN LNK-INT	235
	FLEXFIT HOLDER	541
	FRW	276
	FST	349
G	GD-DH	721
	GD-DH (12-13.5)	723
	GD-DHL	722
	GDV	731
	GFIS ER-ER	1058
	GFI ST-ER	1057
	GFT-J	357

G	GIM-C	363
	GIM-J	363
	GIM-W	363
	GM-DG	362
	GP/GPB	697
	GPP	696
	GPS	696
	GSAN	360
	GSFN	361
	GSFU	361
	GSHT	362
	GTI BT-ER (tapping)	1029
	GTI DIN69871-ER (tapping)	956
	GTI ER-ST (tapping)	1056
	GTIN ER-DIN (tapping)	1060
	GTIN ER-ISO (tapping)	1060
	GTIN ER-JIS (tapping)	1061
H	H3P	553
	H400 ER-10	277
	H400 ER-12	277
	H400 ER-M	278
	H400 FR-10	278
	H400 FR-12	279
	H400 FR-16	280
	H400 RNHU	508
	H490 ANK-09C	230
	H490 ANKX 0904-FF	455
	H490 ANKX 1205-FF	456
	H490 ANKX 1706-FF	457
	H490 ANKX/ANCX-09	454
	H490 ANKX/ANCX-12	455
	H490 ANKX/ANCX-17	457
	H490 E90AX-09	18
	H490 E90AX-12	26
	H490 E90AX-17	30
	H490 E90AX-M	18
	H490 E90AX-MM	18
	H490 F90AX-09	190
	H490 F90AX-12	199

H	
H490 F90AX-17	206
H490 SM-12	237
H490 SM-17	243
H600 WXCU	502
H606 ER-M	280
H606 FR-12	281
H606 RXCU 1206	508
H690 E90AX-10	25
H690 EWN	13
H690 F90AX-10	194
H690 F90AX-16	207
H690 FWN	188
H690 TNKX 1606	459
H690 TNKX/TNCX 1005	457
H690 WNHU/WNMU 0705	454
H1200 HXCU 0606	503
HBF-QF	509
HBR-QF	509
HCC-QF	510
HCD-QF	510
HCE	21
HCE-MM	21
HCM D10	257
HCM D12	257
HCM D16	258
HCM D20	258
HCM D25	259
HCM-M	259
HCM-MM	260
HCP-IQ	542
HCR	509
HFP-IQ	574
HM90 ADCR 1505PDFR-P	441
HM90 ADCT 1505	440
HM90 ADCT 1505PDR-CF	440
HM90 ADKT 1505	439
HM90 ADKT 1505PD-W	445
HM90 ADKW 1505PDR	447
HM90 APCR 1605..R-P	451

H	HM90 APCR 2206..R-P	452
	HM90 APCR 100304PDFR-P/DP	435
	HM90 APCR 220605-CS	452
	HM90 APCT 1003	434
	HM90 APKT 1003	434
	HM90 APKT 1003PD-W	438
	HM90 APKW 1003PDR	438
	HM90 AXCR 1505	450
	HM90 E90A-10	22
	HM90 E90AD-15	28
	HM90 E90AD-M-15	29
	HM90 E90A-M-10	24
	HM90 E90A-MM-10	24
	HM90 EAL-15	378
	HM90 EAL-16	377
	HM90 EAL-HSK63A-15	379
	HM90 EAL-HSK63A-16	377
	HM90 F90A-15	203
	HM90 F90AP-10	193
	HM90 FAL-15	379
	HM90 FAL-16	378
	HM90 FAL-16BR	378
	HM90 FAL-22	379
	HM390 E10-80-07	35
	HM390 ETC-07	15
	HM390 ETC-MM	16
	HM390 ETD-15	27
	HM390 ETD-19	29
	HM390 ETD-M	28
	HM390 ETP-04	10
	HM390 ETP-05	11
	HM390 ETP-10	20
	HM390 ETP-C#-10	20
	HM390 ETP-M	20
	HM390 ETP-MM-04	10
	HM390 ETP-MM-05	11
	HM390 FTC-07	187
	HM390 FTD-15	202
	HM390 FTD-19	205

H	
HM390 FTP-10	192
HM390 TCKT/CT 0703	432
HM390 TDKT 1907	433
HM390 TDKT/CT 1505	433
HM390 TPKR 0401	431
HM390 TPKT/CT 0502	432
HM390 TPKT/CT 1003	432
HOE-R06	212
HOF-R06	213
HOF-R07	213
HP ADCR 1906	449
HP ADCR 2207	450
HP ADKT 1906	449
HP ADKT/ADCT 2207	449
HP ANCR 0702PNFR	430
HP ANK-07	230
HP ANKT 0702...-FF	431
HP ANKT/ANCT 0702..PN-R/PNTR	430
HP ANKW 070204PNTR	430
HP E90AN-07	14
HP E90AN-M-07	14
HP E90AN-MM-07	15
HP E90AT-19	31
HP F90AN-07	187
HP F90AT-19	209
HP F90AT-22	209
HSD Fixed Torque Handles	516
HSK A-B-MN (blanks)	987
HSK A-CF (CLICKFIT)	985
HSK A-EM (DIN 1835 Form B)	970
HSK A-EM (DIN 1835 Form E)	971
HSK A-ER	962
HSK A-ER-CLICKIN	984
HSK A-ER-M (mini)	961
HSK A-ER-SHORT	965
HSK A-FM	980
HSK A-HYDRO	966
HSK A-HYDRO HD	969
HSK A-HYDRO (long)	968

H	HSK A-MAXIN	965
	HSK A-MB	830
	HSK A-MT	982
	HSK A-ODP (FLEXFIT)	309, 986
	HSK A-SEM	979
	HSK A-SEM-C	983
	HSK A-SEMC	981
	HSK A-SRK	978
	HSK A-SRKIN	972
	HSK A-SRKIN-CX	974
	HSK-C#	981
	HSK E-ER	960
	HSK E-MB	830
	HSK E-SEM	979
	HSK E-SRK	976
	HSK F-MB	831
	HSK FM-ER	964
	HSK FM-SEM	980
	HSK FM-SRKIN	975
	HSM90S APCR 1405	450
	HSM90S APCR 2207	452
	HSM90S EAL-14	376
	HSM90S FAL-14	376
	HSM90S FAL-22	380
	HSM90SFD-HSK A63/80-22	380
	HTF-R-LN10	190
	HTP-LN06	304
	HTP-LN10	305
	HTP LN.. 0604	512
	HTP LN.. 1006	512
	HTP LN.. 1606	513
	HTP-M-LN06	304
	HTP-M-LN10	305
	HTP-R-LN10	306
	HTP-R-LN16	306
I	ICG	547
	ICN	549
	IFP-IQ	574
	IHAXF	871

I	IHAXF-AVI	873
	IHAXF-E	873
	IHBR	849
	IHCR	848
	IHFF	853
	IHFF-C	852
	IHPR	849
	IHRF	853
	IHRF-BW	877
	IHRF-C	852
	IHRF-CH	878
	IHSR	848
	IHSR-BW	850
	IHSR-C	852
	IHSR-CH	849
	IHSR-MIFR	846
	IHWF	875
	IQ845 ESY-R05	214
	IQ845 FSY-C#-R07	221
	IQ845 FSY-R05	214
	IQ845 FSY-R07	221
	IQ845 SYHU-05	482
	IQ845 SYHU-07	482
	ISO-MB	832
	ISOM-MB	832
K	Key Blades	516
	KIT BHD-MB	879
	KIT BHE MB	881
	KIT BHFH-MB	888
	KIT BHF-MB	885
	KIT BHF MB-BL	884
	KIT BT-HYDRO	1084
	KIT BT-MAXIN	1009
	KIT DIN2080-ER	1034
	KIT DIN69871-HYDRO	1084
	KIT GTI ER-ST	1056
	KIT HSK A-HYDRO	1084
	KIT HSK A-MAXIN	966
	KIT IHAXF	888

K	KIT SK-MAXIN	942
	KIT ST-ER	1040
	KIT ST-ER-M/MF	1038
L	LNAR 1106	466
	LNAR 1106 (PCD)	467
	LNAR 1106PN-R-S-W (PCD)	467
	LNAR 1506	472
	LNAR 1506 PN-R-S (PCD)	473
	LNAT 1106-W	466
	LNAT 1506AN-W	475
	LNAT 1506-PM	474
	LNAT 1506..PN-N MM	473
	LNAT 1506-W	473
	LNAW-11 (CBN)	468
	LNAW-15 (CBN)	469
	LNET 08	477
	LNET 12-TN	477
	LNET 12-TN-MM	478
	LNET 18-M	364
	LNHT 1106 PN-N HT	466
	LNHT 1106 PN-R HT	465
	LNHW 1506 ANTN (ceramic)	475
	LNHW 1506 PNTN (ceramic)	472
	LNKX 1506 1.5X45 PN-N	471
	LNKX 1506PN-N PL	470
	LNKX 150608AN-N PL	474
	LNKX/LNMT 1106	465
	LNKX/LNMT 1506PNTN/PN-N MM	470
	LNKX/LNMT 150608ANTN MM	474
	LNMT 1506PN-R-TS	469
	LNMT/LNHT 1506...-N HT	472
	LNMT/LNHT 1506PN-R HT	471
	LNMW 1506 PNTN	470
	LOGT	723
M	MB-BL-RING	835
	MD-BODY	571
	MD-DFN-HEAD	571
	MD-DR-DH-HEAD	572
	MF EWX	292

M	
MF EWX-M	292
MF FHX-R06	298
MF FWX	297
MIFR	846
MM Adjustable Torque Keys	77
MM CAB	76, 1047
MM CAB-T-T	77
MM EA	69
MM EA-CF	69
MM EB	59
MM EBA	60
MM EBC	59
MM EC-3	61
MM EC-4	62
MM EC-6	63
MM EC-8/10	64
MM EC-CF	65
MM EC-CF-Z4-1.5xD	66
MM EC-CF-Z7/9-1.5xD	64
MM EC-D	63
MM ECD	46
MM ECF	41
MM EC-H-4-CF	65
MM EC-H-5-CF	66
MM ECS	45
MM ECU	61
MM EDF	42
MM EFCB	46
MM EFF	55
MM EFS	66
MM EFS-CF	67
MM EPG	45
MM ER	44
MM ERA	68
MM ERS	67
MM ERS-1.5xD	68
MM ET	57
MM ETR	57
MM FF	54

M	MM FM	51, 186
	MM GRIT-16K/P,18K/P	49, 316
	MM GRIT-22K/P,28K/P	50, 317
	MM GRIT 28P-DR	43
	MM GRIT Dovetail	43, 318
	MM GRIT-K/P-45A	42
	MM GRT (shanks)	72
	MM HBR	58
	MM HC	60
	MM HCD	40
	MM HCR	58
	MM HDF	41
	MM HR	44
	MM HRF	58
	MM HT	56
	MM HT-NCSR	56
	MM HT-NWFR	57
	MM S-A-C#	72
	MM S-A-HSK	76, 985
	MM S-A-N	71
	MM S-A-SK	76, 957
	MM S-A (stepped shanks)	70
	MM S-A (straight shanks)	73
	MM S-B (85° conical shanks)	73
	MM S-D (89° conical shanks)	74
	MM S-ER	75
	MM S-ER-H	75
	MM SS	51
	MM TRD-M	51, 403
	MM TRD-W	52, 403
	MM TS-45	42
	MM TS-A	72
	MM TS-C	48, 315
	MM TS-DG	48, 315
	MM TS-H	47, 314
	MM TS-N	46, 314
	MNC	554
	MNC-7/8D	555
	MNCNT-T2	729

M	MNSNT	730
	MTD-MB	834
	MTECB-ISO	390
	MTECB-NPT	400
	MTECB-PG	401
	MTEC-BSPT	399
	MTECB-UN	394
	MTECB-W	398
	MTECD-ISO	393
	MTEC E-ISO	391
	MTEC E-UN	395
	MTECI-A60	402
	MTECI-ISO	402
	MTEC-ISO	389
	MTEC-NPT	400
	MTEC-NPTF	401
	MTECQ-ISO	390
	MTECSH-ISO	393
	MTECSH-UN	397
	MTECS-ISO	392
	MTECS-MJ	399
	MTECS-UN	396
	MTECS-UNJ	399
	MTECS-W	397
	MTEC-UN	394
	MTEC-W	398
	MTECZ-BSF/BSP	398
	MTECZ-BSPT	400
	MTECZ-ISO	391
	MTECZ-NPTF	401
	MTECZ-UN	395
	MTE D	406
	MTE D-C	407
	MTE D(Double Insert)	407
	MTE-MM	406
	MT-ER	1036
	MTF D(Shell Mill)	408
	MTFLE	408
	MTH-BSPT (int. & ext.)	420

M	MTH-F	421
	MTH-ISO (external)	418
	MTH-ISO (internal)	418
	MTH-NPTF (int. & ext.)	421
	MTH-NPT (int. & ext.)	420
	MTH-UN (external)	419
	MTH-UN (internal)	419
	MTH-W (int. & ext.)	420
	MT-ISO-MM	52, 404
	MT LNH#-ACME (Internal)	417
	MT LNH#-ISO (Internal)	410
	MT LNH#-NPS	415
	MT LNH#-NPSF	416
	MT LNHT-ABUT	416
	MT LNHT-BSPT	415
	MT LNHT-NPT	414
	MT LNHT-NPTF	414
	MT LNUH-ISO (External)	411
	MT LNH#-UN (Internal)	412
	MT LNUH-PG	417
	MT LNUH-UN (External)	413
	MT LNH#-W	413
	MTSRH (endmills)	409
	MTSRH (helical shell mill)	409
	MTT-MB	834
	MT-UN-MM	53, 405
	MT-W-MM	53, 405
	MULTI CLAMP C#	1095
	MULTI CLAMP HSK (A/C, E/F)	1095
N	NPHT-RG	694
	NPMT-L2/R2	693
	NPMT-R1/2-DT	693
	NPMX 0802 RG	692
	NPMX 0803 RB/RG	692
	NUT ER-MINI/UM	1101
	NUT ER-SHORT	1101
	NUT ER-TOP	1100
O	OECR	488
	OEMT 060405	488

O	OEMW-AETN	489
	OFCR/OFCT-AEN/AETN	490
	OFCR/OFCT-RW/AER (wiper)	490
	OFMT 07	489
	OFMW-AETN	489
	OFMW-FF	491
	ONHQ-TN	498
	ONHU 0505-W	487
	ONHU 0706AN-R-W	491
	ONHU 0806AN-W	499
	ONHU 0806-N-PL	499
	ONHU/ONMU-05	487
	ONHU/ONMU-08-TN/HL	498
	ONHU/ONMU-08-TN-MM	498
	ONHU/ONMU 080608 AN-N-HP	499
	ONMU 1008	492
	ONMU/ONHU 0706	491
	OXMT 0507	488
P	P290 ACCT/KT	446
	P290 ACK	236
	P290 ACK-C#-18	236
	P290 ACK-M	235
	P290 ACKT	446
	P290 EPW	30
	P290 EPW-M	31
	P290 FPW/FCT	208
	P290 SM	237
	PICCO ACE-BH	872
	PICCO-MF	624
	PICCO-MFT	625
	PICCO R 050.20	899
	PICCO R 050 (CBN)	901
	PICCO R/L 047	899
	PICCO R/L 050, 053, 055	898
	PICCO R/L 050-C	900
	PICCO R/L 090	900
	PICCO R/L 520	901
	PICCO R/LHD 050	901
	PICCO R/LX050	897

P	PLHT	512
	PLT	902
	PNMT 0602-TN	515
	PRESET ER-JET	1101
	PRESET MAXIN	1102
	PS BT-JIS (pull stud)	1099
	PS BT-MAS (pull stud)	1099
	PS BT-MAZAK (pull stud)	1099
	PS CAT-ISO (pull stud)	1100
	PS OTT-BT (pull stud)	1100
	PS OTT-SK (pull stud)	1100
	PS SK-DIN (pull stud)	1100
Q	QDCT-PDN	481
	QDMT 1205PDN-RM	481
	QDMT 1205..PDTN-M	482
	QOMT-HQ	478
	QPMR 1004-HQ-M	479
	QPMT 100408PDTN	479
R	R8-MB	834
	R90CW	505
	RCMT/RCCT-MO	506
	RCMT/RCMW-FW	507
	RCMW/RCCW-MO	506
	R (drive flange set)	359
	RE-C#	1003
	RE MB-AVI	836
	RE MB-MB	836
	REMT-76	505
	RFMT 1905-76	507
	RGP	695
	RING DCM	614
	RM-BN-H7LB	752
	RM-BN-H7SA	753
	RM-BN-RC-RING	752
	RM-BNT (Shanks)	751
	RM-FCR-H7N-CS-C	761
	RM-FCR-H7S-CS-C	760
	RM-MTR-H7N-CS-C	759
	RM-MTR-H7S-CS-C	758

R	RM-SEI-A	773
	RM-SEI-B	773
	RM-SEI-C	774
	RM-SET-B-B	772
	RM-SET-T-B	771
	RM SETTING DEVICE	774
	RM-SHR-H7N-MT	763
	RM-SHR-H7S-MT	762
	RM-SR-H7S	764
	RM-SRH-Q-MT	764
	RXCR	504
	RXCW	504
	RXMT 10	504
	RXMT 1607	505
S	S845 F45SX-16	222
	S845 SNHU 1305-W	484
	S845 SNHU 1806AN-N-W	485
	S845 SNMU 2608	485
	S845 SNMU/SNHU-13	483
	S845 SNMU/SNHU 1806	485
	S845 SXHU 1606-W	484
	S845 SXMU/SXCU-16	484
	S865 FSN-13	211
	S865 SNMU 1305ZNTR	486
	S890 FSN-13	198
	S890 SNMU 1305PN...	497
	S890 SSB-13	350
	SCCD-AP5	644
	SCD-ACG8 (8xD)	647
	SCD-ACP3N (3xD)	634
	SCD-ACP5 (5xD)	642
	SCD-ACP5N (5xD)	640
	SCD-ACP8 (8xD)	648
	SCD-ACP8N (8xD)	649
	SCD-ACP20 (20xD)	650
	SCD-ACP-CS (20xD)	650
	SCD-AH5 (5xD)	646
	SCD-AP3 (3xD)	632
	SCD-AP3N (3xD)	630

S	SCD-AP4 (4xD)	629
	SCD-AP5 (5xD)	638
	SCD-AP5N (5xD)	636
	SCD-AP6 (6xD)	629
	SCDT	617
	SCGT-AS	895
	SC-HYDRO	1085
	SCMT-14	894
	SCMT-19	496, 895
	SCMT-SM	894
	SCREW EM	1105
	SC-SEAL	1082
	SC-SPR	1082
	SD CAB	320
	SD FM	186
	SD FM-S-A-SP	186
	SDHT/X 120508	456
	SDHW/T 100408	486
	SDK-10-C/HP	243
	SDK-12-C/HP	244
	SD-M-N-SP	364
	SDMR-HQ	481
	SDMT-AD-N	496
	SDMT-PDN-RM	480
	SDMT-PDR-HQ	486
	SDN	348
	SDN-CALN11	346
	SDN-CALN12	344
	SDN-CALN13	347
	SDN-CALN15	349
	SDN-CAPM15	347
	SDN-LN08	342
	SDN-LN12	343
	SDN-XN13	346
	SD S-A-SP	320
	SD-SP	319
	SD TRD-M-SP	403
	SD TRD-W-SP	404
	SECT/SEMT 1404	495

S	SEHT-AFN	493
	SEHW-AFTN	492
	SEKN-AF..	494
	SEKR-AF.-76	494
	SEKR-AF-N-42	494
	SEKR-AFTR-HS	495
	SEKT-AF-R	492
	SEKT-AFTN	493
	SEM Clamping Screws	1102
	SEMT 12..AFTN-76	493
	SEMT 1204AF-R-HS	492
	SET ER-SEAL	1080
	SET ER-SEAL-EM	1081
	SET ER-SEAL-EM JET2	1081
	SET ER-SEAL-JET2	1080
	SET ER-SPR	1080
	SET ER-SPR-AA	1080
	SET ER-SPR-EM	1081
	SET SC-SEAL	1082
	SGP	695
	SGSA	360
	SGSF	358
	SGSF/A-M-JHP	359
	SGSF/A-MM-JHP	360
	SGSF-W	357
	SGST	356
	SKA-FC-MB	829
	SKA-MB	829
	SKB-MB	829
	SLEEVE	872
	S M	304, 1045
	SM	244
	S M-CF	305, 1046
	S M-C-H	304, 1045
	SMH MB	839
	SM-XN13	241
	SOE45 8/16	34
	SOF45	217
	SOF45-26	223

S	SOF45-R18	224
	SOF45WG-R26	223
	SOGT-W	555
	SOGX/T-AL	595
	SOGX-W	555
	SOMT 0402-FF	483
	SOMT/CT 0402	483
	SOMT-DT	596
	SOMT-GF	596
	SOMT-HD	596
	SOMT-HQ	478
	SOMX-DT	595
	SOMX-GF	595
	SOMX-HD	595
	SPK	235
	SPKN ED..	495
	SPKR ED..-76	496
	SPKR EDTR-HS	496
	SPM-D-CA	382
	SPMT-HQ	480
	SRKIN PRESET SCREW	1105
	SSB	350
	SSB-LN15-R/L	350
	ST-ER	1039
	ST-ER-MF-D (double-ended)	1042
	ST-ER-MF (mini flat)	1041
	ST-ER-M (mini)	1038
	ST-MB	833
	ST-MB-E	834
	ST-SRK	1042
	STUB MB	840
	SW-C-D-JHP	356
	SW/S	359
	SW/S-JHP	353
T	T4..-SM Conical Shell Mills	242
	T290 ELN-05	12
	T290 ELN-10	19
	T290 ELN-MM-05	12
	T290 FLN-10	191

T	T290 FLN-15	200
	T290 LNMT 1506	459
	T290 LNMT/LNHT 0502	459
	T290 LNMT/LNHT 1004	459
	T290 SM	230
	T465 FLN-22ST	212
	T465 LNHT/LNMT 2212	476
	T490 CAP-13FT	240
	T490 ELN-08	16
	T490 ELN-11	25
	T490 ELN-13	27
	T490 ELN-16	29
	T490 ELN-C#-13	27
	T490 ELN-M	17
	T490 ELN-MM-08	17
	T490 FLN-08	189
	T490 FLN-11	194
	T490 FLN-13	200
	T490 FLN-16	205
	T490 FLN-22ST	209
	T490 FLN-C#-08	189
	T490 LNAR	464
	T490 LNK-11	232
	T490 LNK-13	232
	T490 LNK-13-BT	233
	T490 LNK-13-C#	233
	T490 LNK-13-CF	233
	T490 LNK-13-INT	234
	T490 LNK-BT-FT	242
	T490 LNK-INT50-FT	241
	T490 LNK-M-13	232
	T490 LNM-08	231
	T490 LNM-M-08	231
	T490 LNMT 1306PNR-FF	463
	T490 LNMT 1306PNTR-FW	463
	T490 LNMT/LNHT 0804	460
	T490 LNMT/LNHT 1106	461
	T490 LNMT/LNHT 1306	462
	T490 LNMT/LNHT 1607	464

T	T490 LNMT/LNHT 2212	476
	T490 SM-08	238
	T490 SM-11	238
	T490 SM-13	239
	T490 SM-13FT	239
	T490 SM-16	243
	T890HT ELN-R13	26
	T890HT FLN-R13	195
	T890 LNHT/LNAT 1306	460
	TAG N-A	355
	TAG N-C/W/M	354
	TAG N-J/JS/JT	355
	TCC-DIN	841
	TCH AL	847, 876
	TCHH EX	877
	TCMT-19	895
	TCMT-SM	896
	TCS-DIN	840
	TDO-I (D18.41-65.00)	701
	TDO-I (D65.00-171.99)	701
	TGSF	352
	TGSF-JHP	353
	TGSF-M-JHP	353
	TGSF-MM-JHP	354
	TJS-GJET-BT	1091
	TJS-GJET-C#	1092
	TJS-GJET-ER32	1091
	TJS-GJET-HSK A63	1091
	TJS-GJET-ST	1092
	TJS HPC BT	1093
	TJS HPC C#	1093
	TJS HPC ER	1092
	TJS HPC HSK	1093
	TJS HPC ST	1093
	TOGT	722
	TOOL CLAMP	1095
	Torx Blades	516
	TPF M-F (HSS)	797
	TPG MF (HSS)	788

T	TPG M-H (HSS)	793
	TPG M (HSS)	787
	TPG M-S (HSS)	793
	TPG UNC (HSS)	789
	TPG UNF (HSS)	789
	TPGX	896
	TPGX (CBN)	897
	TPGX (PCD)	897
	TPH M-W (HSS)	786
	TPKN/TPKR	453
	TP MB-M	840
	TPMT	453
	TPMX	692
	TPS MF (HSS)	791
	TPS M-H (HSS)	795
	TPS M (HSS)	790
	TPS M-N (HSS)	794
	TPST MF-G (HSS)	796
	TPST M-G (HSS)	796
	TPS UNC (HSS)	792
	TPS UNF (HSS)	792
	TR6 ER	267
	TR6 ER-M	269
	TR6 FR	271
	TR6 TNCU/MU	514
	TR45 TXMT	515
	TR90 TXMT	515
	TRFF TXMT	515
	TRI	476
	TRIB	321
	TRIB-SM	322
	TS***	697
	TS-I**	698
	TS-O**	699
W	WCGT	896
	WRENCH COOL TUBE C#	1106
	WRENCH ER	1102
	WRENCH HSK	1105
	WRENCH MAXIN	1102

W	WRENCH SEMC	1103
X	XCGT-DT	617
	XCMT-MF	619
	XCMT-MG	620
	XNK-XN13	234
	XNMU 13	497
	XOGX-DT	614
	XOMT-HQ	479
	XPMT-45	693
	XPMT-HQ	480
	XPMT-UB	693

ISCAR LTD.**Israel****Headquarters**

Tel +972 (0) 04 997 0311
 Fax+972 (0) 04 987 3741
www.iscar.com
headquarter@iscar.co.il

Argentina

ISCAR TOOLS ARGENTINA SA
 Tel +54 114 912 2200
 Fax+54 114 912 4411
admin@iscararg.com.ar
www.iscararg.com.ar

Australia

ISCAR AUSTRALIA PTY. LTD
 Tel +61 (0) 2 8848 3500
 Fax+61 (0) 2 8848 3511
iscaraus@iscar.com.au
www.iscar.com.au

Austria

ISCAR AUSTRIA GmbH
 Tel +43 7252 71200-0
 Fax+43 7252 71200-999
office@iscar.at
www.iscar.at

Belarus

JV ALC "TWING-M"
 Tel +375 17 506-32-38
 +375 17 506-33-31/65
 Tel/Fax +375 17 506-32-37
info@twing.by
www.twing.by, www.iscar.by

Belgium

n.v. ISCAR BENELUX s.a.
 Tel +32 (0) 2 464 2020
 Fax+32 (0) 2 522 5121
info@iscar.be
www.iscar.be

Bosnia

(Representative Office)
 Tel +387 32 201 100
 Fax+387 32 201 101
info@iscar.ba

Brazil

ISCAR DO BRASIL COML. LTDA.
 Tel +55 19 3826-7100
 Fax+55 19 3826-7171
 DDG 0800 701 8877
iscar@iscarbrasil.com.br
www.iscar.com.br

Bulgaria

ISCAR BULGARIA
 Tel/Fax +359 431 62557
aa_iscar@infotel.bg
www.iscar.bg

Canada

ISCAR TOOLS INC.
 Tel +1 905 829 9000
 Fax+1 905 829 9100
admin@iscar.ca
www.iscar.ca

Chile

SANDE SA
 Tel +56 2 695 1700
 Fax +56 2 697 0332
logistica@sande.cl

China

ISCAR CHINA
 Tel +86 10 6561 0261/2/3
 Fax+86 10 6561 0264
iscar@iscar.com.cn
www.iscar.com.cn

Colombia

CIMEX S.A.
 Tel: +57 (1) 530-9222
cimex@cimexsa.com

DUROMETAL COLOMBIA
 Tel: +57 1 674 03 20
 Fax: +57 1 674 04 03
dirventas@duro-metal.com

Croatia

ISCAR ALATI d.o.o.
 Tel +385 (0) 1 33 23 301
 Fax +385 (0) 1 33 76 145
iscar@zg.t-com.hr
www.iscar.hr

Cyprus

WAMET (Demetriadis) Ltd.
 Tel +357 (0) 2 336660/5498
 Fax +357 (0) 2 333386
wamet@cytanet.com.cy

Czech Republic

ISCAR CR s.r.o.
 Tel +420 377 420 625
 Fax +420 377 420 630
iscar@iscar.cz
www.iscar.cz

Denmark

KJ VAERKTØEJ AS/ISCAR DENMARK
 Tel +45 70 11 22 44
 Fax++45 46 98 67 10
kj@kj.dk
www.iscar.dk

Estonia

KATOMSK AS
 Tel +372 6775 671
 Fax +372 6720 266
aleksei@katomsk.ee

Finland

ISCAR FINLAND OY
 Tel +358-(0)9-439 1420
 Fax +358-(0)9-466 328
info@iscar.fi
www.iscar.fi

France

ISCAR FRANCE SAS
 Tel +33 (0) 30 12 92 92
 Fax+33 (0) 30 12 95 82
info@iscar.fr
www.iscar.fr

Germany

ISCAR GERMANY GmbH
 Tel +49 (0) 72 43 9908-0
 Fax+49 (0) 72 43 9908-93
gmbh@iscar.de
www.iscar.de

Greece

INTERNATIONAL TOOLS
 K.-X. GEORGOPoulos & SIA O.E
 Tel +30 210 346 0133
 Fax +30 210 342 5621
info@internationaltools.gr

VIMA

V. MAZLOUMIAN & SONS
 Tel +30 2310 517-117 / 544-521
 Fax +30 2310 529-107
vimaco@otenet.gr
<http://www.vimaco.gr>

Hong Kong

MTC TOOLING SYSTEMS LTD
 Tel +85-2-23054838
 Fax +85-2-27988789
yoongkamsing@hotmail.com

Hungary

ISCAR HUNGARY KFT.
 Tel +36 28 887 700
 Fax +36 28 887 710
iscar@iscar.hu
www.iscar.hu

India

ISCAR India Ltd.
 Tel +91 77009 63707
crao@iscar.in

Indonesia

CV MULTI TEKNIK
 Tel. +62-21-29206242/44/45/49
 Fax. +62-21-29206243
contact@multi-teknik.co.id

Ireland

HARDMETAL MACHINE TOOLS
 Tel +353 (0) 1 286 2466
 Fax +353 (0) 1 286 1514
phannigan@hardmetal.ie

Italy

ISCAR ITALIA srl
 Tel +39 02 93 528 1
 Fax +39 02 93 528 213
marketing@iscaritalia.it
www.iscaritalia.it

Japan

ISCAR JAPAN LTD.
 Tel +81 6 6833 5471
 Fax +81 6 6835 5472
iscar@iscar.co.jp
www.iscar.co.jp

Latvia

SIA EKL/LS
 Tel +371 6 733 11 54
 Fax +371 6 780 56 48
eklpstools@isr.lv

Lithuania

MECHA, UB
 Tel +370 37 407 230
 Fax +370 37 407 231
sigitas@mecha.lt

Macedonia

(Representative Office)
 ISCAR DE MÉXICO
 Tel +389 2 309 02 52
 Fax +389 2 309 02 54
info@iscar.com.mk

Mexico

ISCAR DE MÉXICO
 Tel +52 (442) 214 5505
 Fax+52 (442) 214 5510
iscarmex@iscar.com.mx
www.iscar.com.mx

The Netherlands

ISCAR NEDERLAND B.V.
 Tel +31 (0) 182 535523
 Fax+31 (0) 182 572777
info@iscar.nl
www.iscar.nl

New Zealand

ISCAR PACIFIC LTD.
 Tel +64 (0) 9 573 1280
 Fax+64 (0) 9 573 0781
iscar@iscarpac.co.nz

Norway

SVEA MASKINER AS
 Tel +47 3227750
 Fax+47 3227751
per.martin.bakken@svea.no

Peru

HARTMETALL SAC
 Tel: (511) 6612699
otorres@hartmetallgroup.com

Philippines

MESCO
 Tel +63 2631 1775
 Fax +63 2635 0276
mesco@mesco.com.ph

Poland

ISCAR POLAND Sp. z o.o.
 Tel +48 32 735 7700
 Fax+48 32 735 7701
iscar@iscar.pl
www.iscar.pl

Portugal

ISCAR PORTUGAL, SA
 Tel +351 256 579950
 Fax+351 256 586764
info@iscarportugal.pt
www.iscarportugal.pt

Romania

ISCAR TOOLS SRL
 Tel +40 (0)312 286 614
 Fax+40 (0)312 286 615
iscar-romania@iscar.com

Russia

Moscow
 ISCAR RUSSIA LLC
 Tel/fax +7 495 660 91 25/31
iscar@iscar.ru
www.iscar.ru

Chelyabinsk

ISCAR RUSSIA EAST LLC
 Tel/fax +7 351 277 74 32
info@iscar-east.com
www.iscar-east.ru

Serbia

ISCAR TOOLS d.o.o.
 Tel +381 11 314 90 38
 Fax +381 11 314 91 47
info@iscartools.rs

Singapore

SINO TOOLING SYSTEM
 Tel +65 6566 7668
 Fax +65 6567 7336
sinotool@singnet.com.sg

Slovakia

ISCAR SR, s.r.o.
 Tel +421 (0) 41 5074301
 Fax +421 (0) 41 5074311
info@iscar.sk
www.iscar.sk

Slovenia

ISCAR SLOVENIJA d.o.o.
 Tel +386 1 580 92 30
 Fax+386 1 562 21 84
info@iscar.si
www.iscar.si

South Africa

ISCAR SOUTH AFRICA (PTY) LTD.
 ShareCall 08600-47227
 Tel +27 11 997 2700
 Fax +27 11 388 9750
iscarsa.co.za
www.iscar.co.za

South Korea

ISCAR KOREA
 Tel +82 53 760 7594
 Fax+82 53 760 7500
leeyj@taegutec.co.kr
www.iscarkorea.co.kr

Spain

ISCAR IBERICA SA
 Tel +34 93 594 6484
 Fax +34 93 582 4458
iscar@iscarib.es
www.iscarib.es

Sweden

ISCAR SVERIGE AB
 Tel +46 (0) 18 66 90 60
 Fax +46 (0) 18 122 920
info@iscar.se
www.iscar.se

Switzerland

ISCAR HARTMETALL AG
 Tel +41 (0) 52 728 0850
 Fax +41 (0) 52 728 0855
office@iscar.ch
www.iscar.ch

Taiwan

ISCAR TAIWAN LTD.
 Tel +886 (0)4-24731573
 Fax +886 (0)4-24731530
iscar.taiwan@msa.hinet.net
www.iscar.org.tw

Thailand

ISCAR THAILAND LTD.
 Tel +66 (2) 7136633-8
 Fax+66 (2) 7136632
iscar@iscarthailand.com
www.iscarthailand.com

Turkey

ISCAR KESICI TAKIM
 TIC. VE. IML. LTD
 Tel +90 (262) 751 04 84 (Pbx)
 Fax+90 (262) 751 04 85
iscar@iscar.com.tr
www.iscar.com.tr

Ukraine

ISCAR UKRAINE LLC
 Tel/fax +38 (044) 503-07-08
iscar_ua@iscar.com
www.iscar.com.ua

United Kingdom

ISCAR TOOLS LTD.
 Tel +44 (0) 121 422 8585
 Fax+44 (0) 121 423 2789
sales@iscar.co.uk
www.iscar.co.uk

United States

ISCAR METALS INC.
 Tel +1 817 258 3200
 Tech Tel 1-877-BY-ISCAR
 Fax+1 817 258 3221
info@iscarmetals.com
www.iscarmetals.com

Venezuela

FERREINDUSTRIAL ISO-DIN C.A.
 Tel +58 2 632 8211/633 4657
 Fax +58 2 632 5277
iso-din@cantv.net

Vietnam

ISCAR VIETNAM
 (Representative Office)
 Tel +84 8 38 123 519/20
 Fax +84 8 38 123 521
iscarvn@hcm.fpt.vn
www.iscarvn.com

© 2013 Iscar Ltd. This document, as well as all information and other data contained herein and/or derived therefrom, including but not limited to, all trademarks, logos, trade-names, concepts, pictures, designs and/or devices, as well as any data from which any proprietary and/or intellectual property right may emanate ("Information"), is the sole and exclusive property of Iscar Ltd. and is protected by copyright and other applicable laws. No part of any Information may be used or otherwise disseminated for any purpose whatsoever without the express prior written consent of Iscar Ltd.

Items appearing in this catalog may be improved, amended or withdrawn without prior notice."

Please check ISCAR's online catalog www.iscar.com for the most current technical information regarding our products.

04/2019



3374300 G

Complete Machining Solutions

Rotating Tool Lines

Milling • Hole Making • Tooling Systems

Metric Version Catalog 2019

